

L63 – 4 Hole Closed 45° Corner Angle

Available Finishes / Materials:

AL -- Aluminum

EG -- Electro-galvanized

GN -- Green Powder Coat

HD -- Hot dipped galvanized

S4 -- 304 stainless steel

S6 -- 316 stainless steel


YC -- Yellow chromate

Standard Finish: EG

Catalog Number	"A"
L63 0000EG	45°
L63 0030EG	30°
L63 0060EG	60°

* "A" is available in any angle up to 90°

Dimensions shown may vary based on specified angle "A"



Catalog Number: L63 0000EG Weight: 0.93 Lbs.

Material is 15/8" [41.3] wide x 1/4" [6.3] thick unless specified. Holes are 3/6" (14.3) diameter, 13/6" [20.6] center to edge on 17/8" [47.6] centers unless specified.

Material Specifications and Finishes

Carbon Steel - ASTM A1011-00 SS GR 33 or ASTM A1011-00CS Type B

- AL Aluminum ASTM B209 (Type 5052-H32)
- EG Electro-Galvanized. Electroplating deposits zinc on the surface of the steel by electrolysis from a bath of zinc salts. Recommended for relatively dry indoor use. This is the standard coating for most Phoenix products. Thickness of applied zinc is between 0.2 mils to 0.5 mils [5.1 μm to 12.7 μm]. Coatings on Phoenix EG products meet ASTM B633 SC1 Type III.
- GN Green Powder Coat. A Polyester powder coating is electrostatically applied after fabrication. The powder is then baked on creating a 1.38 to 1.77 mil [35 45 μm] thick coating. The hardness of this coating meets ASTM D-3363-74, the impact rating meets ASTM D-2794-93 and the gloss meets ASTM D-523-85. This creates a coating that is resistant to chipping, peeling and corrosion. Available in many colors by special order
- HD Hot Dip Galvanized After Fabrication. Fabricated product is dipped in molten zinc and is completely covered on all surfaces. Recommended for outdoor use. Coatings on Phoenix HD products meet ASTM A123/153. The zinc coating is typically 2.6 mils [66.0 μm] or 1.5 oz. per square foot [0.46 kg per square meter] per side.

- S4 304 Stainless Steel ASTM A240 (Type 304)
- S6 316 Stainless Steel ASTM A240 (Type 316), 316 Stainless Steel Nuts – ASTM A276-03
- YC Yellow Zinc Dichromate. A 0.5 mil [12.7 µm] electro-galvanized zinc plating meeting ASTM B633 SC1 Type III is applied to the surface of the metal. Yellow Dichromate is applied over the zinc. This results in a yellowish gold appearance and acts as a nonporous barrier sealant that is corrosion resistant and can be painted.

Note: Specifications subject to change without notice.

Project:	Date:	Phone:
Submited By:	Address:	
Comment	<u> </u>	