


Edited by Nicola Pinna and Mato Knez

 WILEY-VCH

# Atomic Layer Deposition of Nanostructured Materials



#### The Editors

**Prof. Dr. Nicola Pinna**

Department of Chemistry and CICECO  
University of Aveiro  
Campus Universitario de Santiago  
3810-193 Aveiro  
Portugal

and

School of Chemical and Biological Engineering  
College of Engineering  
Seoul National University (SNU)  
151-744 Seoul  
Korea

**Dr. Mato Knez**

MPI für Mikrostrukturphysik  
Experimental Dept. II  
Weinberg 2  
06120 Halle  
Germany

All books published by Wiley-VCH are carefully produced. Nevertheless, authors, editors, and publisher do not warrant the information contained in these books, including this book, to be free of errors. Readers are advised to keep in mind that statements, data, illustrations, procedural details or other items may inadvertently be inaccurate.

**Library of Congress Card No.:** applied for

**British Library Cataloguing-in-Publication Data**

A catalogue record for this book is available from the British Library.

**Bibliographic information published by the Deutsche Nationalbibliothek**

The Deutsche Nationalbibliothek lists this publication in the Deutsche Nationalbibliografie; detailed bibliographic data are available on the Internet at <http://dnb.d-nb.de>.

© 2012 Wiley-VCH Verlag & Co. KGaA,  
Boschstr. 12, 69469 Weinheim, Germany

All rights reserved (including those of translation into other languages). No part of this book may be reproduced in any form – by photoprinting, microfilm, or any other means – nor transmitted or translated into a machine language without written permission from the publishers. Registered names, trademarks, etc. used in this book, even when not specifically marked as such, are not to be considered unprotected by law.

**Typesetting** Thomson Digital, Noida, India

**Printing and Binding** Fabulous Printers Pte Ltd, Singapore

**Cover Design** Grafik-Design Schulz, Fußgönheim

Printed in Singapore  
Printed on acid-free paper

**Print ISBN:** 978-3-527-32797-3

**ePDF ISBN:** 978-3-527-63993-9

**eBook ISBN:** 978-3-527-63991-5

**ePub ISBN:** 978-3-527-63992-2

**mobi ISBN:** 978-3-527-63994-6

## Contents

Foreword	V
Preface	XVII
Introduction	XXI
List of Contributors	XXXIII

### Part One Introduction to ALD 1

<b>1</b>	<b>Theoretical Modeling of ALD Processes</b>	<b>3</b>
	<i>Charles B. Musgrave</i>	
1.1	Introduction	3
1.2	Overview of Atomistic Simulations	3
1.2.1	Quantum Simulations	4
1.2.2	Wave Function-Based Quantum Simulations	5
1.2.3	Density Functional-Based Quantum Simulations	6
1.2.4	Finite and Extended Quantum Simulations	8
1.2.5	Basis Set Expansions	9
1.3	Calculation of Properties Using Quantum Simulations	10
1.3.1	Calculation of Transition States and Activation Barriers	10
1.3.2	Calculation of Rates of Reaction	12
1.4	Prediction of ALD Chemical Mechanisms	13
1.4.1	Gas-Phase Reactions in ALD	14
1.4.2	Surface Reactions in ALD	14
1.4.2.1	Adsorption Reactions in ALD	14
1.4.2.2	Ligand Exchange Reactions	15
1.5	Example of a Calculated ALD Mechanism: ALD of $\text{Al}_2\text{O}_3$ Using TMA and Water	16
	References	20
<b>2</b>	<b>Step Coverage in ALD</b>	<b>23</b>
	<i>Sovan Kumar Panda and Hyunjung Shin</i>	
2.1	Introduction	23
2.2	Growth Techniques	24
2.3	Step Coverage Models in ALD	28

2.3.1	Gordon's Model for Step Coverage	28
2.3.1.1	Parameters for Step Coverage	28
2.3.2	Kim's Model for Step Coverage	31
2.4	Experimental Verifications of Step Coverage Models	34
2.5	Summary	38
	References	38
<b>3</b>	<b>Precursors for ALD Processes</b>	<b>41</b>
	<i>Matti Putkonen</i>	
3.1	Introduction	41
3.2	General Requirements for ALD Precursors	42
3.3	Metallic Precursors for ALD	42
3.3.1	Inorganic Precursors	44
3.3.1.1	Elemental Precursors	44
3.3.1.2	Halides	44
3.3.1.3	Oxygen-Coordinated Compounds	44
3.3.1.4	Nitrogen-Coordinated Precursors	46
3.3.1.5	Precursors Coordinated through Other Inorganic Elements	46
3.3.2	Organometallic ALD Precursors	47
3.3.2.1	Metal Alkyls	47
3.3.2.2	Cyclopentadienyl-Type Compounds	47
3.3.2.3	Other Organometallic Precursors	49
3.4	Nonmetal Precursors for ALD	49
3.4.1	Reducing Agents	49
3.4.2	Oxygen Sources	49
3.4.3	Nitrogen Sources	50
3.4.4	Sulfur and Other Chalcogenide Precursors	50
3.5	Conclusions	50
	References	51
<b>4</b>	<b>Sol-Gel Chemistry and Atomic Layer Deposition</b>	<b>61</b>
	<i>Guyllaine Clavel, Catherine Marichy, and Nicola Pinna</i>	
4.1	Aqueous and Nonaqueous Sol-Gel in Solution	61
4.1.1	Aqueous Sol-Gel	61
4.1.1.1	Introduction	61
4.1.1.2	Development of Sol-Gel Chemistry	61
4.1.2	Nonaqueous Sol-Gel	62
4.1.2.1	Introduction	62
4.1.2.2	Synthesis of Nanomaterials	63
4.2	Sol-Gel and ALD: An Overview	63
4.2.1	Metal Oxide Formation via Hydrolytic Routes	64
4.2.1.1	Reaction with Metal Halides	64
4.2.1.2	Reaction with Metal Alkoxide	65
4.2.1.3	Reaction with Organometallic Compounds	66
4.2.2	Metal Oxide Deposition under Nonaqueous Conditions	67



4.2.2.1	Alkyl Halide Elimination	67
4.2.2.2	Ether Elimination	68
4.2.2.3	Ester Elimination	68
4.2.2.4	Other Reactions	69
4.2.3	Concluding Remarks	69
4.3	Mechanistic and <i>In Situ</i> Studies	70
4.3.1	General Considerations	71
4.3.1.1	Differences between Sol-Gel in Solution and in ALD	71
4.3.1.2	Reaction Mechanism Study	71
4.3.2	Comparison of Selected Reactions	72
4.3.2.1	Case of the Silica Deposition	72
4.3.2.2	Case of Alkyl Halide Condensation	75
4.3.3	Conclusions	76
	References	76
<b>5</b>	<b>Molecular Layer Deposition of Hybrid Organic-Inorganic Films</b>	<b>83</b>
	<i>Steven M. George, B. Yoon, Robert A. Hall, Aziz I. Abdulagatov, Zachary M. Gibbs, Younghee Lee, Dragos Seghete, and Byoung H. Lee</i>	
5.1	Introduction	83
5.2	General Issues for MLD of Hybrid Organic-Inorganic Films	85
5.3	MLD Using Trimethylaluminum and Ethylene Glycol in an AB Process	87
5.4	Expansion to an ABC Process Using Heterobifunctional and Ring-Opening Precursors	89
5.5	Use of a Homotrifunctional Precursor to Promote Cross-Linking in an AB Process	93
5.6	Use of a Heterobifunctional Precursor in an ABC Process	96
5.7	MLD of Hybrid Alumina-Siloxane Films Using an ABCD Process	99
5.8	Future Prospects for MLD of Hybrid Organic-Inorganic Films	103
	References	106
<b>6</b>	<b>Low-Temperature Atomic Layer Deposition</b>	<b>109</b>
	<i>Jens Meyer and Thomas Riedl</i>	
6.1	Introduction	109
6.2	Challenges of LT-ALD	110
6.3	Materials and Processes	113
6.4	Toward Novel LT-ALD Processes	115
6.5	Thin Film Gas Diffusion Barriers	117
6.6	Encapsulation of Organic Electronics	119
6.6.1	Encapsulation of Organic Light Emitting Diodes	119
6.6.2	Encapsulation of Organic Solar Cells	123
6.7	Conclusions	125
	References	125

<b>7</b>	<b>Plasma Atomic Layer Deposition</b>	<b>131</b>
	<i>Erwin Kessels, Harald Profijt, Stephen Potts, and Richard van de Sanden</i>	
7.1	Introduction	131
7.2	Plasma Basics	134
7.3	Plasma ALD Configurations	139
7.4	Merits of Plasma ALD	142
7.5	Challenges for Plasma ALD	149
7.6	Concluding Remarks and Outlook	153
	References	154
<b>Part Two</b>	<b>Nanostructures by ALD</b>	<b>159</b>
<b>8</b>	<b>Atomic Layer Deposition for Microelectronic Applications</b>	<b>161</b>
	<i>Cheol Seong Hwang</i>	
8.1	Introduction	161
8.2	ALD Layers for Memory Devices	162
8.2.1	Mass Production Level Memories	162
8.2.1.1	Dynamic Random Access Memory	163
8.2.1.2	Flash Memory	168
8.2.1.3	Phase Change Memory	172
8.2.2	Emerging Memories	174
8.2.2.1	Ferroelectric Memory	175
8.2.2.2	Magnetic Random Access Memory	178
8.2.2.3	Resistive Random Access Memory	178
8.2.3	Three-Dimensional Stacked Memories	179
8.3	ALD for Logic Devices	180
8.3.1	Front End of the Line Process	180
8.3.2	Back End of the Line Process	185
8.4	Concluding Remarks	187
	References	188
<b>9</b>	<b>Nanopatterning by Area-Selective Atomic Layer Deposition</b>	<b>193</b>
	<i>Han-Bo-Ram Lee and Stacey F. Bent</i>	
9.1	Concept of Area-Selective Atomic Layer Deposition	193
9.2	Change of Surface Properties	195
9.2.1	Self-Assembled Monolayers	195
9.2.2	Polymers	201
9.2.3	Inherent Surface Reactivity	203
9.2.4	Vapor-Phase Deposition	204
9.3	Patterning	205
9.3.1	Surface Modification without Patterning	205
9.3.2	Microcontact Printing	205
9.3.3	Photolithography	207
9.3.4	Nanotemplating	212
9.3.5	Scanning Probe Microscopy	213

9.4	Applications of AS-ALD	215
9.5	Current Challenges	216
	References	218
<b>10</b>	<b>Coatings on High Aspect Ratio Structures</b>	<b>227</b>
	<i>Jeffrey W. Elam</i>	
10.1	Introduction	227
10.2	Models and Analysis	228
10.2.1	Analytical Method	229
10.2.2	Monte Carlo Simulations	229
10.3	Characterization Methods for ALD Coatings in High Aspect Ratio Structures	230
10.4	Examples of ALD in High Aspect Ratio Structures	232
10.4.1	Aspect Ratio of 10	232
10.4.1.1	Trenches	232
10.4.1.2	MEMS	233
10.4.2	Aspect Ratio of 100	234
10.4.2.1	Anodic Aluminum Oxide	234
10.4.2.2	Inverse Opals	237
10.4.3	Aspect Ratio of 1000 and Beyond	238
10.4.3.1	Silica gel	238
10.4.3.2	Aerogels	240
10.5	Nonideal Behavior during ALD in High Aspect Ratios	242
10.6	Conclusions and Future Outlook	245
	References	246
<b>11</b>	<b>Coatings of Nanoparticles and Nanowires</b>	<b>251</b>
	<i>Hong Jin Fan and Kornelius Nielsch</i>	
11.1	ALD on Nanoparticles	251
11.2	Vapor-Liquid-Solid Growth of Nanowires by ALD	254
11.3	Atomic Layer Epitaxy on Nanowires	256
11.4	ALD on Semiconductor NWs for Surface Passivation	257
11.5	ALD-Assisted Formation of Nanopeapods	258
11.6	Photocorrosion of Semiconductor Nanowires Capped by ALD Shell	260
11.7	Interface Reaction of Nanowires with ALD Shell	261
11.7.1	ZnO-Al <sub>2</sub> O <sub>3</sub>	261
11.7.2	ZnO-TiO <sub>2</sub>	262
11.7.3	ZnO-SiO <sub>2</sub>	264
11.7.4	MgO-Al <sub>2</sub> O <sub>3</sub>	265
11.8	ALD ZnO on NWs/Tubes as Seed Layer for Growth of Hyperbranch	265
11.9	Conclusions	267
	References	268

<b>12</b>	<b>Atomic Layer Deposition on Soft Materials</b>	<b>271</b>
	<i>Gregory N. Parsons</i>	
12.1	Introduction	271
12.2	ALD on Polymers for Passivation, Encapsulation, and Surface Modification	274
12.3	ALD for Bulk Modification of Natural and Synthetic Polymers and Molecules	279
12.4	ALD for Polymer Sacrificial Templating: Membranes, Fibers, and Biological and Optical Structures	280
12.5	ALD Nucleation on Patterned and Planar SAMs and Surface Oligomers	283
12.6	Reactions during $\text{Al}_2\text{O}_3$ ALD on Representative Polymer Materials	286
12.6.1	$\text{Al}_2\text{O}_3$ ALD on Polypropylene	286
12.6.2	$\text{Al}_2\text{O}_3$ ALD on Polyvinyl Alcohol	288
12.6.3	$\text{Al}_2\text{O}_3$ ALD on Polyamide 6	289
12.6.4	Mechanisms for $\text{Al}_2\text{O}_3$ ALD on PP, PVA, and PA-6	290
12.7	Summary	291
	References	292
<b>13</b>	<b>Application of ALD to Biomaterials and Biocompatible Coatings</b>	<b>301</b>
	<i>Mato Knez</i>	
13.1	Application of ALD to Biomaterials	302
13.1.1	Protein-Based Nanostructures	302
13.1.1.1	Tobacco Mosaic Virus	302
13.1.1.2	Ferritin and Apoferritin	304
13.1.1.3	S-Layers	304
13.1.2	Peptide Assemblies	305
13.1.3	Natural Fibers	307
13.1.3.1	DNA	307
13.1.3.2	Collagen	308
13.1.3.3	Spider Silk	308
13.1.3.4	Cellulose Fibers from Paper	310
13.1.3.5	Cotton Fibers	310
13.1.3.6	Sea Mouse Bristles	311
13.1.4	Patterned Biomaterials	312
13.1.4.1	Butterfly Wings	312
13.1.4.2	Fly Eyes	314
13.1.4.3	Legumes	315
13.1.4.4	Water Strider Legs	315
13.1.5	Biom mineralized Structures	316
13.2	Biocompatible Coatings	317
13.2.1	Biocompatibility of Alumina	317
13.2.2	Biocompatibility of Titania	318
13.2.3	Biocompatibility of Hydroxyapatite	318

13.2.4	Biocompatibility of Pt-, TiO <sub>2</sub> -, or ZnO-Coated Porous Alumina	318
13.2.5	Biocompatibility of TiN-Coated Cotton Fabrics	319
13.3	Summary	320
	References	321
<b>14</b>	<b>Coating of Carbon Nanotubes</b>	<b>327</b>
	<i>Catherine Marichy, Andrea Pucci, Marc-Georg Willinger, and Nicola Pinna</i>	
14.1	Introduction	327
14.2	Purification and Surface Functionalization of Carbon Nanotubes	328
14.3	Decoration/Coating of Carbon Nanotubes by Solution Routes	329
14.3.1	<i>In Situ</i> Coating	329
14.3.2	Attachment of Preformed Nanobuilding Blocks	330
14.4	Decoration/Coating of Carbon Nanotubes by Gas-Phase Techniques	330
14.5	Atomic Layer Deposition on Carbon Nanotubes	331
14.6	Coating of Large Quantity of CNTs by ALD	337
14.7	ALD Coating of Other sp <sup>2</sup> -Bonded Carbon Materials	338
14.8	Conclusions	340
	References	340
<b>15</b>	<b>Inverse Opal Photonics</b>	<b>345</b>
	<i>Davy P. Gaillot and Christopher J. Summers</i>	
15.1	Introduction and Background	345
15.2	Properties of Three-Dimensional Photonic Band Structures	349
15.2.1	Synthetic Opals and Inverse Opals	349
15.3	Large-Pore and Non-Close-Packed Inverse Opals	352
15.4	Experimental Studies	353
15.4.1	Inversion of Opal Structures	353
15.4.2	Atomic Layer Deposition	357
15.4.3	Multilayer Fabrication Steps for Advanced Photonic Crystals	360
15.5	Tunable PC Structures	366
15.6	Summary	369
	References	371
<b>16</b>	<b>Nanolaminates</b>	<b>377</b>
	<i>Adriana V. Szeghalmi and Mato Knez</i>	
16.1	Introduction	377
16.2	Optical Applications	377
16.2.1	Interference Optics	377
16.2.2	Diffraction Optical Elements	381
16.3	Thin Film Encapsulation	383
16.4	Applications in Electronics	386
16.4.1	Dielectric Properties of Inorganic Nanolaminates	387
16.4.2	Dielectric Properties of Organic-Inorganic Nanolaminates	390

16.4.3	Applications for Memories	391
16.5	Copper Electroplating Applications	392
16.6	Solid Oxide Fuel Cells	393
16.7	Complex Nanostructures	394
16.8	Summary	395
	References	396

## 17 Challenges in Atomic Layer Deposition 401

Markku Leskelä

17.1	Introduction	401
17.2	Metals	402
17.3	Nonmetal Elements	404
17.4	Binary Compounds	406
17.4.1	Oxides	406
17.4.2	Nitrides	408
17.4.3	Other III–V Compounds	410
17.4.4	Carbides	410
17.4.5	Silicides and Borides	412
17.4.6	Halides	412
17.4.7	Compounds with Oxoanions	413
17.5	Ternary and Quaternary Compounds	414
17.6	Nucleation	415
17.7	Conclusions	416
	References	417

## Index 423

## 3

**Precursors for ALD Processes***Matti Putkonen*

## 3.1

**Introduction**

Since atomic layer deposition (ALD) is a chemical gas-phase thin film deposition method based on sequential, self-saturating surface reactions, the selection of the suitable reactants, that is, precursors, is extremely critical. Typically, two or more chemical precursors are needed, each containing different elements of the materials being deposited. Precursors are adsorbed onto the substrate surface separately. Each precursor saturates the surface forming a monolayer of material and purging between reactants excludes gas-phase reactions. Process temperatures range from room temperature to over 500 °C. The largest selection of ALD processes operates around 300 °C. ALD processes have been developed for oxides, nitrides, carbides, fluorides, certain metals, II–VI and III–V compounds, and recently also for the organic materials [1].

Development of new ALD precursors and processes has been very active over the past 35 years at several universities, R&D centers, and companies. ALD was first demonstrated for the TFEL application by ZnS deposition using elemental zinc and sulfur in mid 1970s, followed by the use of  $\text{ZnCl}_2$  and  $\text{H}_2\text{S}$  [1]. After the initial period, several other precursor types have emerged. During the second half of 1980s, metal-organic precursors were also adapted for ALD [2, 3]. This opened plenty of possibilities for new ALD chemistry and processes. A large number of ALD processes have been demonstrated and published up to date, and the list is growing all the time.

In this chapter, different precursors used in ALD are discussed in detail. Generally, ALD processes can be divided according to ligand types used in the volatile precursors. The volatile metal-containing precursors typically fall into the following categories: elemental precursors, inorganic precursors, and organometallic ALD precursors. These classes are discussed in detail and some examples of chemical surface reactions are provided.

### 3.2

#### General Requirements for ALD Precursors

Although ALD resembles chemical vapor deposition (CVD) quite closely, the requirements for ALD precursors differ from other chemical gas-phase methods since all gas-phase reactions should be excluded and reactions should occur only at the surface. In the early history of ALD, CVD reactants were also used, but nowadays specific tailor-made precursors often provide better results [4, 5]. For example, the use of different exchange reactions at the surface makes it possible to create novel ways to produce challenging thin film materials other than traditional oxides and nitrides. ALD growth mode allows the use of significantly more reactive precursors than CVD. In CVD methods, a constant flow of the precursor vapor is needed to obtain a controlled process, but because ALD relies on self-limiting reactions, only a limited amount of the precursor is required during one pulse to cover the adsorption sites on the surface; the excess amount is removed during the inert gas purge or pumpdown. This makes it possible to use, in some cases, *in situ* generation of the metal precursors and thus have a fresh supply of otherwise instable precursor molecules onto the substrate surface [6, 7]. This technique has been successfully applied to produce  $\beta$ -diketonate compounds of alkaline earth metals (Sr, Ba) by pulsing ligand vapor over heated metal or metal hydroxide [8].

In order to avoid uncontrolled reactions, sufficient thermal stability of the precursors is needed in the gas phase as well as on the substrate surface within the deposition temperature range, which is typically 150–450 °C. Because ALD is a gas-phase process, solid and liquid precursors must be volatile under the operating temperature and pressure, and if heating is required to obtain sufficient vapor pressure, thermal stability of the precursor over a prolonged time is necessary. Stability is the key issue especially when coating porous materials or nanostructures requiring long precursor diffusion times.

There are some general requirements for ALD precursors:

- sufficient volatility at the deposition temperature;
- no self-decomposition or reaction on itself at the deposition temperature;
- precursors must adsorb or react with the surface sites;
- sufficient reactivity toward the other precursors;
- no etching of the substrate or the growing film;
- availability at a reasonable price;
- safe handling and preferably nontoxicity.


Quite often, the ALD precursors do not fulfill all of these requirements. Moreover, sensitive substrates may give additional limitations to precursor selection.

### 3.3

#### Metallic Precursors for ALD

In the ALD of inorganic materials, at least one metal-containing precursor is needed (Scheme 3.1). Recently, the ALD process has also been applied to organic materials





**Scheme 3.1** Examples of precursors for ALD depositions. Volatile halides (a), alkoxides (b), and  $\beta$ -diketonates (c) are traditionally used as ALD precursors. Organometallic precursors such as metal alkyls (d) and homo- and heteroleptic cyclopentadienyl-type compounds (e and f) have often favorable properties.

Nitrogen-coordinated compounds such as metal amides (g), silylamides (h), amidinates (i), and guanidates (i, if  $R = NR_2$ ) have also been successfully applied to ALD. More recently, alkylsilyl compounds (j) and pyrazolyl borate-type ligands (k) have been used for the demanding ALD processes.

and inorganic/organic hybrid materials, and it is now referred to as molecular layer deposition (MLD) and its features will be discussed in detail in Chapter 5.

### 3.3.1

#### Inorganic Precursors

Inorganic precursors offer low-cost alternatives for many ALD processes. In some cases, they have suffered film contamination or etching but still their thermal stability makes possible the use of relatively high deposition temperatures. Most common of these are metal halides, but other inorganic precursors such as metal nitrates, carboxylates, and isocyanates have also been tested [9–11].

##### 3.3.1.1 Elemental Precursors

The early ALD processes utilized either volatile elements such as zinc and sulfur or halides [1]. The low volatility of pure elements limits the number of applicable processes or forces the use of very high deposition temperatures. However, deposition rates are quite high since there are no sterical hindrances in the elemental precursor.

##### 3.3.1.2 Halides

The most common inorganic precursors are metal halides. Several metal halide precursors have been applied in ALD processes, together with water, ammonia, and hydrogen sulfide as a second reactant. However, the suitability of a particular metal halide for ALD depositions has been found to depend on the metal precursor reactivity. Metal chlorides such as  $\text{TiCl}_4$  [12–14],  $\text{ZrCl}_4$  [15, 16], and  $\text{HfCl}_4$  [17–19] are commonly used as ALD precursors, but metal fluorides [20], bromides [21], and iodides [22] have also been successfully applied. Generally, halide precursors are quite thermally stable, so relatively high deposition temperatures can be applied. However, halide contamination of the film may cause problems at low deposition temperatures [23]. Liberation of  $\text{HX}$  ( $\text{X} = \text{F}, \text{Cl}, \text{Br}, \text{I}$ ) during the deposition process may also cause problems, such as corrosion and etching.

Oxyhalides are another type of volatile inorganic precursors, which have been used in only a few studies. For instance, tungsten oxyfluoride ( $\text{WO}_x\text{F}_y$ ) and  $\text{H}_2\text{O}$  have been used as precursors in the deposition of  $\text{WO}_3$  [7], while  $\text{CrO}_2\text{Cl}_2$  has been used in the deposition of chromium oxide [24, 25].

##### 3.3.1.3 Oxygen-Coordinated Compounds

$\beta$ -Diketonate-type compounds are perhaps the most common oxygen-coordinated precursors for ALD. These metal chelates are known for their volatility and relative stability and therefore they were originally synthesized for the separation of metals by fractional sublimation [26] and gas chromatography [27]. In the 1970s, they were utilized for the first time in CVD depositions [28].  $\beta$ -Diketonates in ALD processes were first utilized in the 1980s as dopant precursors (e.g., for Tb, Ce, Eu, and Th) for  $\text{ZnS}$  [29] and other sulfide thin films [30] since halides for these dopants suffered low vapor pressures. Somewhat later, they were applied in metal oxide depositions [31], but quite high deposition temperatures are required to obtain favorable reaction with

water, hydrogen peroxide, or oxygen. Another approach is to use a strong oxidizing agent, such as ozone.

Metal  $\beta$ -diketonates have also been studied for the deposition of metals [32–34], metal nitrides [35], and metal sulfides [36]. However, since they have metal to oxygen bond present, there might be some oxygen residues present in the deposited films. Impurity levels depend a lot on the material itself; for example,  $\text{Y}(\text{thd})_3 + \text{H}_2\text{S}$  precursor combination leads to yttrium oxysulfide [37], whereas  $\text{In}(\text{acac})_3 + \text{H}_2\text{S}$  leads to  $\text{In}_2\text{S}_3$  [38].

Recently, metal  $\beta$ -diketonates have also been applied to the deposition of metal fluorides ( $\text{MgF}_2$ ,  $\text{CaF}_2$ ,  $\text{LaF}_3$ ) using metal  $\beta$ -diketonates as metal precursors and solid  $\text{TiF}_4$  or  $\text{TaF}_5$  as a fluoride source [39]. This reaction proceeds through ligand exchange reaction between the metal  $\beta$ -diketonate and the metal fluoride. This reaction produces titanium or tantalum  $\beta$ -diketonates as volatile by-products. Another way to deposit fluoride thin films is by using fluorinated metal  $\beta$ -diketonates such as  $\text{Ca}(\text{hfac})_2$  or metal  $\beta$ -diketonates with separate fluorine source such as  $\text{HF}$  [40] or  $\text{Hhfac}$  (1,1,1,5,5,5-hexafluoroacetylacetonate) [41].

It has been observed in CVD and ALD that coordinatively unsaturated  $\beta$ -diketonate-type compounds may oligomerize or react with the moisture and become less volatile [6, 8]. This is observed especially with large and basic metal centers such as strontium and barium.  $\beta$ -Diketonate-type chelates can be protected against oligomerization and hydrolysis by adducting them with a neutral molecule [42].

With adducted precursors, volatilization behavior during heating depends on the choice of metal, ligand, and adduct and on the bond strengths between them. Adducted precursors may sublime in a single-step process, or alternatively they may dissociate during heating, releasing the neutral adduct, which leads to a two-stage volatilization process where the second step corresponds to the sublimation of the original unadducted compound [43]. ALD depositions of sulfide films have been carried out using  $\text{Ca}(\text{thd})_2(\text{tetraen})$  or  $\text{Ce}(\text{thd})_3(\text{phen})$ , where the growth process appears to be similar to that of the unadducted precursor [44]. Similar results have also been obtained in the case of deposition process for  $\text{Y}_2\text{O}_3$  films from  $\text{Y}(\text{thd})_3(\text{phen})$ ,  $\text{Y}(\text{thd})_3(\text{bipy})$ , and  $\text{O}_3$  as precursors [45]. It seems that, even if sublimation at one stage is observed, the adducted precursors dissociate at the deposition temperatures, producing the unadducted precursor [44].

Another interesting group of oxygen-coordinated metal precursors includes the metal alkoxides. They are usually more thermally unstable than  $\beta$ -diketonate compounds [46, 47], but offer lower evaporation temperatures. Titanium precursors such as  $\text{Ti}(\text{OCH}_3)_4$  [48],  $\text{Ti}(\text{OCH}_2\text{CH}_3)_4$  [49], and  $\text{Ti}(\text{O}^i\text{Pr})_4$  [50, 51] have been shown to be especially useful when depositing ternary strontium-containing materials to suppress the formation of strontium chloride impurities originating from the  $\text{TiCl}_4$  precursor [52, 53].

Although simple alkoxide ligands can be used for some elements, metal alkoxides also offer rather straightforward possibility to modify the ligands in order to tailor the ALD process behavior and film properties [54]. For example, bulkier ligands such as *t*-butoxide [55, 56], 1-methoxy-2-methylpropan-2-ol [57], 1-dimethylamino-2-methyl-2-propanolate [58], and dimethylaminoethoxide [59] have been successfully applied

for ALD deposition of metal oxides. Even  $\text{SiO}_2$  can be deposited by using  $\text{H}_2\text{N}(\text{CH}_2)_3\text{Si}(\text{OEt})_3$  or  $\text{Si}(\text{OCH}_2\text{CH}_3)_4$  as a silicon precursor [60, 61]. Recently, copper bis(dimethylamino)-2-propoxide has been applied for deposition of metallic copper films [62]. This reaction is based on the exchange reactions with diethylzinc leading to volatile  $\text{Zn}(\text{dmap})_2$  by-product and copper films.

#### 3.3.1.4 Nitrogen-Coordinated Precursors

Another quite interesting class of ALD precursors includes nitrogen-coordinated compounds such as metal alkylamides and metal amidinates. They have been applied to ALD only recently and there are still emerging possibilities for these precursors. The biggest drawback for some of these compounds is the limited thermal stability.

The most common metal alkylamides are the ones developed for zirconium and hafnium.  $\text{M}(\text{NMe}_2)_4$ ,  $\text{M}(\text{NMeEt})_4$ , and  $\text{M}(\text{NEt}_2)_4$  ( $\text{M} = \text{Zr}, \text{Hf}$ ) can be used for the deposition of corresponding oxide and nitride films [63, 64]. Corresponding tantalum alkylamides show stability comparable to zirconium and hafnium, but titanium alkylamides seem to be too unstable to be used in ALD [65, 66]. Other alkylamides studied in ALD include dimethylamides of aluminum, gallium, germanium, antimony [67], and tungsten and alkylimidoalkylamides of tungsten and molybdenum [68, 69], for example. Recently, different aminosilanes have been studied for the deposition of silicon oxides and nitrides, such as bis(dimethylamino)silane [70], tris(dimethylamino)silane [71], and tetraethylsilaneamine [72].

Metal silylamides provide new opportunities for the selection of ALD materials but they are usually more thermally unstable compared to the corresponding metal alkylamides.  $\text{Ce}[\text{N}(\text{SiMe}_3)_2]_3$  was applied for the first time in ALD for growing electroluminescent  $\text{SrS}:\text{Ce}$  thin films [73]. More recently,  $\text{M}[\text{N}(\text{SiMe}_3)_2]_3$  complexes have been utilized in the ALD of  $\text{LaO}_x$ ,  $\text{PrO}_x$ , and  $\text{GdO}_x$  as well as bismuth-containing films [74, 75]. In addition,  $\text{ZrCl}_2[\text{N}(\text{SiMe}_3)_2]_2$  has been used for  $\text{ZrO}_2$  thin films at relatively low temperatures [76]. In addition, the biggest drawback is that one possible decomposition pathway can lead to silicon impurities in the films.

Metal amidinates have been studied for the deposition of several metals and metal oxides [77]. Amidinates are structurally analogous to the carboxylates, except that the ligand is coordinating through nitrogen, making these compounds more reactive than the corresponding chelates coordinating through oxygen. For example, recently bis( $N,N'$ -di-*tert*-butylacetamidinato)ruthenium [78], lanthanum tris( $N,N'$ -diisopropylacetamidinate) [65], and tris( $N,N$ -diisopropylformamidinato)lanthanum [66] have been used as ALD precursors. A special group of  $\eta^2$ -coordinated compounds includes guanidinates. For example,  $\text{Gd}_2\text{O}_3$  films have been deposited by using  $\text{Gd}(\text{PrN})_2\text{CNMe}_2$  as metal precursor [79]. In addition, heteroleptic guanidinate-based precursors such as  $\text{Hf}(\text{NEtMe})_2(\text{EtMeNC}(\text{N}^i\text{Pr})_2)_2$  have been used in ALD [80].

#### 3.3.1.5 Precursors Coordinated through Other Inorganic Elements

Although most of the inorganic ALD precursors are halides and N- or O-coordinated compounds, other precursor classes are also emerging. For example, boron-coordinated precursors such as bis(tris(3,5-diethylpyrazolyl)borate)barium have been used for growing barium borate thin films [81].

Recently introduced silicon-coordinated compounds offer interesting route for complex materials. Alkylsilyl tellurium and selenium precursors make it possible to deposit  $\text{Ge}_2\text{Sb}_2\text{Te}_5$  and  $\text{CuInSe}_2$  [82].

### 3.3.2

#### Organometallic ALD Precursors

By IUPAC definition, organometallic compounds have bonding between at least one carbon atom and the metal atom. The chemistry of organometallic compounds has been studied for almost 200 years and the ALD relevant cyclopentadienyl compounds have been known from the beginning of the 1950s. During the past few years, the volatility and high reactivity of organometallics have been exploited in ALD. First, ALD processes exploiting organometallic precursors were studied using metal alkyls as precursors. Later on, various compounds containing cyclopentadienyl or other bulkier ligands have been successfully utilized.

##### 3.3.2.1 Metal Alkyls

ALD processes based on organometallic precursors were first developed for the GaAs depositions by using either  $(\text{CH}_3)_3\text{Ga}$  [83, 84] or  $(\text{CH}_3\text{CH}_2)_3\text{Ga}$  [85] and  $\text{AsH}_3$  as an arsenic source. Analogous indium alkyls, mainly  $(\text{CH}_3)_3\text{In}$ , have been used to deposit InAs [86], InP [87], and  $\text{In}_2\text{O}_3$  [88] thin films.

Aluminum alkyls, for example,  $(\text{CH}_3)_3\text{Al}$ ,  $(\text{CH}_3)_2\text{AlH}$ , and  $(\text{CH}_3\text{CH}_2)_3\text{Al}$ , have been used for the deposition of several III–V materials, such as AlAs [89], AlP [90], and AlN [91], using  $\text{AsH}_3$ ,  $\text{PH}_3$ , and  $\text{NH}_3$  as second precursors, respectively. The most common use of aluminum alkyls (e.g.,  $(\text{CH}_3)_3\text{Al}$ ,  $(\text{CH}_3)_2\text{AlCl}$  [92],  $(\text{CH}_3)_2\text{AlH}$  [93], or  $(\text{CH}_3\text{CH}_2)_3\text{Al}$ ) is for the deposition of  $\text{Al}_2\text{O}_3$  thin films.  $\text{Al}_2\text{O}_3$  is probably the most frequently studied ALD-processed material since  $(\text{CH}_3)_3\text{Al}$  has been used with  $\text{H}_2\text{O}$  [94],  $\text{H}_2\text{O}_2$  [95],  $\text{NO}_2$ , [96]  $\text{N}_2\text{O}$ , [97],  $\text{O}_2$  plasma [98], or  $\text{O}_3$  [99] as an oxygen source.

Transparent conductive  $\text{SnO}_2$  has been deposited using  $(\text{CH}_3)_4\text{Sn}$  or  $(\text{CH}_3\text{CH}_2)_4\text{Sn}$  as a metal precursor and  $\text{N}_2\text{O}_4$  as an oxygen source [100]. In order to dope  $\text{SnO}_2$  films,  $\text{BF}_3$  pulses were added to the processes resulting in almost two orders of magnitude higher conductivity of the as-deposited material. In a similar manner, zinc alkyls, for example,  $(\text{CH}_3)_4\text{Zn}$  and  $(\text{CH}_3\text{CH}_2)_4\text{Zn}$ , have been used as ALD precursors for ZnS [101], ZnSe [102], and ZnTe [103] thin films with  $\text{H}_2\text{S}$ ,  $\text{H}_2\text{Se}$ , and  $\text{H}_2\text{Te}$  as chalcogen sources, respectively. In addition, they have been utilized for the deposition of ZnO thin films using  $\text{H}_2\text{O}$  as an oxygen source and have also been doped with boron [104], gallium [105], or aluminum [106] from  $\text{B}_2\text{H}_6$ ,  $(\text{CH}_3)_3\text{Ga}$ , or  $(\text{CH}_3)_3\text{Al}$ , respectively. Furthermore,  $(\text{CH}_3\text{CH}_2)_4\text{Pb}$  has been utilized as an ALD precursor for PbS thin films with  $\text{H}_2\text{S}$  as the second precursor [107].

##### 3.3.2.2 Cyclopentadienyl-Type Compounds

Chemistry of cyclopentadienyl compounds is studied for almost every element [108]. The main application is their use as catalysts, but they are also suitable for use as precursors in MOCVD [109]. Although cyclopentadienyl compounds have attracted

considerable interest as precursors in CVD depositions, they are sometimes too reactive [110]. However, high reactivity and thermal stability make cyclopentadienyl compounds very attractive precursors for ALD, where high reactivity can be controlled by sequential pulsing of the precursors.

For group 2 (Be, Mg, Sr, Ba) elements, several different Cp precursors are utilized. For example,  $(C_5H_5)_2Mg$  has been successfully used in the ALD deposition of MgO thin films [111, 112]. Because of the larger size of the heavier alkaline earth metals, simple  $(C_5H_5)_2Sr$  and  $(C_5H_5)_2Ba$  compounds are not suitable for ALD. Therefore, deposition of strontium- and barium-containing films has been studied by using bulkier ligands. For example,  $SrTiO_3$  and  $BaTiO_3$  thin films have been deposited from  $(C_5^tPr_3H_2)_2Sr$ ,  $(C_5Me_5)_2Ba$ , and  $(C_5^tBu_3H_2)_2Ba$  as alkaline earth metal precursors and  $Ti(OCH(CH_3)_2)_4$  and  $H_2O$  as titanium and oxygen sources, respectively [113]. In addition, SrS and BaS thin films have been deposited from  $(C_5^tPr_3H_2)_2Sr$ ,  $(C_5Me_5)_2Sr$ , and  $(C_5Me_5)_2Ba$  using  $H_2S$  as the second reactant [114].

The smallest cyclopentadienyl compounds of the series can be utilized in ALD rather straightforwardly for lanthanide elements [115], but thermal stability of the corresponding lanthanum and cerium compounds needs more precursor tailoring. Generally, bulkier ligands will protect the metal central better and decrease the tendency of thermal decomposition. Recently,  $La^tPrCp)_3$  has been successfully utilized for  $La_2O_3$  deposition [116].  $(C_5Me_4H)_3Ce$  has been successfully used for the doping of ALD-grown SrS thin films [117]. More recently, mixed ligand-type Cp compounds have also been applied [118].

Several volatile cyclopentadienyl-type compounds of group 4 elements have been utilized in ALD. First organometallic ALD experiments to process  $ZrO_2$  and  $HfO_2$  thin films were carried out using  $(C_5H_5)_2MCl_2$  and  $(C_5H_5)_2M(CH_3)_2$  [119, 120]. Additional heteroleptic compounds of Ti, Zr, and Hf containing alkoxy [121, 122] or N-coordinated ligands [123, 124] have been successfully used as precursors.

Only few other transition metal cyclopentadienes have been studied in ALD. For example, volatile  $(C_5H_5)_2Mn$  and  $(C_5MeH_4)Mn(CO)_3$  have been used as manganese sources for doping ZnS thin films to produce yellow-emitting thin film electroluminescent devices as well as for the deposition of MnO [125]. In addition, ferrocene has been utilized for the deposition of  $Fe_2O_3$  thin films [126] and CpIn for  $In_2O_3$  [127]. A different approach has been utilized for processing metallic nickel thin films by ALD [128]. During the first stage, NiO thin films were deposited by one ALD cycle of  $(C_5H_5)_2Ni$  and  $H_2O$ . The NiO layer formed was then reduced to metallic nickel by pulsing hydrogen radicals into the reactor. Nickel and cobalt can also be deposited by three-stage deposition using an oxidizer followed by hydrogen as a reducing agent [129] or directly using a plasma-enhanced process [130].

Cyclopentadienyl precursors for noble metals have gained significant interest. Typically, oxygen or air is used as a second reactant in these processes [131]. These processes are based on the fact that  $O_2$  does not oxidize the noble metal film, but only decomposes the organic ligand. Adsorbed oxygen atoms react with the ligands of the noble metal precursor during the metal precursor pulse [132]. For example, Ru films have been deposited from  $(C_5H_5)_2Ru$  [132] or  $(C_5EtH_4)_3Ru$  [133]. If longer oxidizer pulses or additional energy is used, for example, in the form of plasma, noble metal

oxides (e.g.,  $\text{RuO}_2$  and  $\text{PtO}_2$ ) can also be deposited [134, 135]. Deposition of platinum metal films has been studied in a similar manner using  $(\text{C}_5\text{MeH}_4)\text{PtMe}_3$  and  $\text{O}_2$  as precursors [136], but  $\beta$ -diketonate-type precursors can also be used [137], as shown in Section 3.3.1.3.

#### 3.3.2.3 Other Organometallic Precursors

In addition to metal alkyls and cyclopentadienyl compounds, other types of true organometallic precursors have also been applied to ALD. For example,  $(\text{C}_6\text{H}_5)_3\text{Bi}$  [138, 139] and  $(\text{C}_6\text{H}_5)_4\text{Pb}$  [139] have been used for the preparation of bismuth- and lead-containing oxide thin films. These compounds are not extremely reactive and therefore ozone is needed [138, 139]. Metallic bismuth was observed as an impurity if  $\text{H}_2\text{O}_2$  was used as an oxygen source [138].

### 3.4

#### Nonmetal Precursors for ALD

Because reactants are separated in the ALD process, it is possible to control the reactivity and the reactions between the precursors by using different precursor combinations. In addition to traditional ALD deposition mechanism that is based on metal and nonmetal precursors, more innovative reaction mechanisms have also been developed. For example, metal alkoxides have been used as oxygen sources [140]. No separate oxygen source is needed in this type of special process because the metal alkoxide serves as both metal and oxygen sources. Other reactions such as ALD mechanism based on the catalytic precursors [61, 141], ligand exchange reactions [39], or replacement reactions at the surface [142] have also been developed.

#### 3.4.1

##### Reducing Agents

Sometimes a reducing precursor is needed although in many ALD processes no redox reactions occur and the oxidation state of the metal does not change. Hydrogen is perhaps the most widely used reducing agent, but metallic zinc vapor [143], different silanes [144], TMA [145], and  $\text{B}_2\text{H}_6$  [146] have also been successfully applied. Molecular hydrogen is quite inert toward typical metal precursors and therefore either high deposition temperatures or plasma is needed to maintain ALD reactions.

#### 3.4.2

##### Oxygen Sources

Typically in the case of ALD-processed oxide films, precursors attached to the surface can be transformed to the respective oxide with  $\text{H}_2\text{O}$ ,  $\text{H}_2\text{O}_2$  [147],  $\text{N}_2\text{O}_4$  [100],  $\text{N}_2\text{O}$  [96],  $\text{O}_2$  [126], or  $\text{O}_3$  [148], the choice depending on the metal precursor reactivity or desired properties. Water has frequently been used as an oxygen source and indeed it readily reacts with many metal precursors. Alcohols have also been successfully

applied as oxygen sources in processes involving inorganic precursors and alkoxides. For example, deposition of  $\text{Al}_2\text{O}_3$  has been carried out with an  $\text{AlCl}_3$  and ROH precursor combination, where R is H,  $\text{CH}_3$ ,  $\text{CH}_2\text{OHCH}_2\text{OH}$ ,  $t\text{-C}_4\text{H}_9\text{OH}$ , or  $n\text{-C}_4\text{H}_9\text{OH}$  [149].

The high thermal stability of the  $\beta$ -diketonate-type complexes or low reactivity of cyclopentadienyl-based precursors usually does not allow their use in ALD with mild oxygen sources. The use of  $\text{H}_2\text{O}$ ,  $\text{H}_2\text{O}_2$ ,  $\text{N}_2\text{O}$ ,  $\text{CH}_3\text{COOH}$ , and  $\text{O}_2$  has been explored for  $\beta$ -diketonate-type compounds [150, 151], but the reactivities are usually insufficient, producing either no film growth or films with a high impurity content. The use of a strong oxidizer, such as  $\text{O}_3$  or oxygen plasma, guarantees that only a small amount of carbon is left in the film as residues and can also improve the film properties [152, 153].

#### 3.4.3

##### Nitrogen Sources

Deposition of nitride thin films by ALD requires both a nitrogen source and a reducing agent in order to obtain clean surface reactions [154]. In many cases, one compound, for example,  $\text{NH}_3$ , serves as both a nitrogen source and a reducing agent. In addition, other nitrogen-containing compounds such as  $\text{N}_2\text{H}_4$ ,  $(\text{CH}_3)_3\text{NNH}_2$ ,  $t\text{-BuNH}_2$ , and  $\text{CH}_2\text{CHCH}_2\text{NH}$  have also been studied as nitrogen sources [155, 156]. Ammonia has been used for depositing several nitride materials such as TiN,  $\text{Ta}_3\text{N}_5$ ,  $\text{W}_2\text{N}$ , NbN, and WCN thin films by ALD [157]. Quite often, plasma processes are utilized due to low reactivity of ammonia as well as need for lower resistivity films [158, 159].

#### 3.4.4

##### Sulfur and Other Chalcogenide Precursors

For chalcogenide thin films, it is possible to use elemental S, Se, and Te as precursors provided that the other source is volatile and reactive enough [160]. ZnS deposition using elemental zinc and sulfur was the first ALD process developed. For other than elemental metal precursors, the reactivity of elemental chalcogens is often not sufficient. For halides,  $\beta$ -diketonates, and organometallics, simple hydrides such as  $\text{H}_2\text{S}$ ,  $\text{H}_2\text{Se}$ , and  $\text{H}_2\text{Te}$  have been typically used as a second precursor [161, 162]. Due to the toxicity of these materials, *in situ* generation of  $\text{H}_2\text{S}$  has been studied by using thioacetamide decomposition [163]. Recently, different alkylsilylamines with lower toxicity have also been developed for Se and Te [82].

### 3.5

#### Conclusions

Since atomic layer deposition is a chemical gas-phase method, its success relies on the development of well-behaving ALD precursors. Although a number of good ALD



processes are available, there is still room for improvement. Conventional inorganic precursors have been used since the beginning of the ALD era over some 35 years ago. To replace the classical precursors, for example, volatile halides and inorganic complexes, organometallics and nitrogen-coordinated precursors are widening the ALD process selection at the moment. Recent developments of metal processes and other "difficult" materials confirm that novel processes are constantly emerging. Nevertheless, additional research is still needed to develop special precursors and further improve process and thin film quality. In the future, more precursors and processes relying on smart reaction mechanisms are expected to appear.

## References

- 1 Ritala, M. and Niinistö, J. (2009) Atomic layer deposition, in *Chemical Vapour Deposition: Precursors, Processes and Applications* (eds A.C. Jones and M.L. Hitchman), Royal Society of Chemistry, pp. 158–206.
- 2 Higashi, G.S. and Rothberg, L.J. (1985) Surface photochemical phenomena in laser chemical vapor deposition. *J. Vac. Sci. Technol. B*, **3**, 1460–1463.
- 3 Higashi, G.S. and Fleming, C.G. (1989) Sequential surface chemical reaction limited growth of high quality  $\text{Al}_2\text{O}_3$  dielectrics. *Appl. Phys. Lett.*, **55** (19), 1963–1965.
- 4 Leskelä, M. and Ritala, M. (1999) ALD precursor chemistry: evolution and future challenges. *J. Phys. IV*, **9**, Pr8-837–Pr8-852.
- 5 Härsta, A. (1999) Precursor selection in halide CVD of oxides. *Chem. Vapor Depos.*, **5** (4), 191–193.
- 6 Soininen, P., Nykänen, E., Niinistö, L., and Leskelä, M. (2004) Atomic layer epitaxy of strontium sulfide thin films using *in situ* synthesized strontium precursors. *Chem. Vapor Depos.*, **2** (2), 69–74.
- 7 Tägtström, P., Mårtensson, P., Jansson, U., and Carlsson, J.-O. (1999) Atomic layer epitaxy of tungsten oxide films using oxyfluorides as metal precursors. *J. Electrochem. Soc.*, **146** (8), 3139–3143.
- 8 Saanila, V., Ihanus, J., Ritala, M., and Leskelä, M. (1998) Atomic layer epitaxy growth of BaS and BaS:Ce thin films from *in situ* synthesized  $\text{Ba}(\text{thd})_2$ . *Chem. Vapor Depos.*, **4** (6), 227–233.
- 9 Badot, J.C., Ribes, S., Yousfi, E.B., Vivier, V., Pereira-Ramos, J.P., Baffier, N., and Lincot, D. (2000) Atomic layer epitaxy of vanadium oxide thin films and electrochemical behavior in presence of lithium ions. *Electrochem. Solid-State Lett.*, **3** (10), 485–488.
- 10 Niskanen, A., Hatanpää, T., Arstila, K., Leskelä, M., and Ritala, M. (2007) Radical-enhanced atomic layer deposition of silver thin films using phosphine-adducted silver carboxylates. *Chem. Vapor Depos.*, **13** (8), 408–413.
- 11 Kobayashi, K. and Okudaira, S. (1997) Preparation of ZnO films on sapphire (0001) substrates by alternate supply of zinc acetate and  $\text{H}_2\text{O}$ . *Chem. Lett.*, **6**, 511–512.
- 12 Ritala, M., Leskelä, M., Nykänen, E., Soininen, P., and Niinistö, L. (1993) Growth of titanium dioxide films by atomic layer epitaxy. *Thin Solid Films*, **225**, 288–295.
- 13 Tiznado, H. and Zaera, F. (2006) Mechanistic details of atomic layer deposition (ALD) processes for metal nitride film growth. *J. Phys. Chem. B*, **110** (27), 13491–13498.
- 14 Kubala, N.G., Rowlette, P.C., and Wolden, C.A. (2009) Plasma-enhanced atomic layer deposition of anatase  $\text{TiO}_2$  using  $\text{TiCl}_4$ . *J. Phys. Chem. C*, **113** (37), 16307–16310.
- 15 Ritala, M. and Leskelä, M. (1994) Zirconium dioxide thin films deposited by ALE using zirconium tetrachloride as precursor. *Appl. Surf. Sci.*, **75** (1–4), 333–340.

- 16 Niinistö, J., Kukli, K., Heikkilä, M., Ritala, M., and Leskelä, M. (2009) Atomic layer deposition of high- $k$  oxides of the group 4 metals for memory applications. *Adv. Eng. Mater.*, **11** (4), 223–234.
- 17 Ritala, M., Leskelä, M., Niinistö, L., Prohaska, T., Friedbacher, G., and Grasserbauer, M. (1994) Development of crystallinity and morphology in hafnium dioxide thin films grown by atomic layer deposition. *Thin Solid Films*, **250** (1–2), 72–80.
- 18 Delabie, A., Pourtois, G., Caymax, M., De Gendt, S., Ragnarsson, L.-A., Heyns, M., Fedorenko, Y., Swerts, J., and Maes, J.W. (2007) Atomic layer deposition of hafnium silicate gate dielectric layers. *J. Vac. Sci. Technol. A*, **25**, 1302–1308.
- 19 Nyns, L., Delabie, A., Pourtois, G., Van Elsocht, S., Vinckier, C., and De Gent, S. (2010) Study of the surface reactions in ALD hafnium aluminates. *J. Electrochem. Soc.*, **157** (1), G7–G12.
- 20 Scharf, T.W., Prasad, S.V., Dugger, M.T., Kotula, P.G., Goeke, R.S., and Grubbs, R.K. (2006) Growth, structure, and tribological behavior of atomic layer-deposited tungsten disulphide solid lubricant coatings with applications to MEMS. *Acta Mater.*, **54** (18), 4731–4743.
- 21 Putkonen, M., and Niinistö, L. (2006) Atomic layer deposition of  $B_2O_3$  thin films at room temperature. *Thin Solid Films*, **514** (1–2), 145–149.
- 22 Rosental, A., Tarre, A., Gerst, A., Sundqvist, J., Härsta, A., Aidla, A., Aarik, A., Sammelselg, V., and Uustare, T. (2003) Gas sensing properties of epitaxial  $SnO_2$  thin films prepared by atomic layer deposition. *Sens. Actuators B*, **93** (1–3), 552–555.
- 23 Aarik, J., Aidla, A., Kiisler, A.-A., Uustare, T., and Sammelselg, V. (1999) Influence of substrate temperature on atomic layer growth and properties of  $HfO_2$  thin films. *Thin Solid Films*, **340** (1–2), 110–116.
- 24 Tarre, A., Aarik, J., Mändar, H., Niilisk, A., Pärna, R., Rammula, R., Uustare, T., Rosental, A., and Sammelselg, V. (2008) Atomic layer deposition of  $Cr_2O_3$  thin films: effect of crystallization on growth and properties. *Appl. Surf. Sci.*, **254** (16), 5149–5256.
- 25 Ezhovskii, Yu.K. and Kholkin, V.Yu. (2008) Formation and some properties of chromium oxide nanolayers on semiconductors. *Russ. Microelectron.*, **37** (6), 356–417.
- 26 Berg, E.W. and Acosta, J.J.C. (1968) Fractional sublimation of the  $\beta$ -diketone chelates of the lanthanide and related elements. *Anal. Chim. Acta*, **40**, 101–113.
- 27 Eisentraut, K.J. and Sievers, R.E. (1965) Volatile rare earth chelates. *J. Am. Chem. Soc.*, **87** (22), 5254–5254.
- 28 Ben-Dor, L., Druilhe, R., and Gibart, P. (1974) Thin films of binary metal oxides by chemical vapor deposition from organometallic chelates. *J. Cryst. Growth*, **24–25**, 172–174.
- 29 Tammenmaa, M., Leskelä, M., Koskinen, T., and Niinistö, L. (1986) Zinc sulphide thin films doped with rare earth ions. *J. Less-Common Met.*, **126**, 209–214.
- 30 Tammenmaa, M., Antson, H., Asplund, M., Hiltunen, L., Leskelä, M., and Niinistö, L. (1987) Alkaline earth sulfide thin films grown by atomic layer epitaxy. *J. Cryst. Growth*, **84** (1), 151–154.
- 31 Aarik, J., Aidla, A., Jaek, A., Leskelä, M., and Niinistö, L. (1994) Precursor properties of calcium  $\beta$ -diketonate in vapor phase atomic layer epitaxy. *Appl. Surf. Sci.*, **75** (1–4), 33–38.
- 32 Hämäläinen, J., Puukilainen, E., Kemell, M., Costelle, L., Ritala, M., and Leskelä, M. (2009) Atomic layer deposition of iridium thin films by consecutive oxidation and reduction steps. *Chem. Mater.*, **21** (20), 4868–4872.
- 33 Niskanen, A., Rahtu, A., Sajavaara, T., Arstila, K., Ritala, M., and Leskelä, M. (2005) Radical-enhanced atomic layer deposition of metallic copper thin films. *J. Electrochem. Soc.*, **152** (1), G25–G28.
- 34 Kim, S.K., Hoffmann-Eifert, S., and Waser, R. (2009) Growth of noble metal Ru thin films by liquid injection atomic layer deposition. *J. Phys. Chem. C*, **113** (26), 11329–11335.
- 35 Törndahl, T., Ottosson, M., and Carlsson, J.-O. (2006) Growth of copper(I) nitride by ALD using copper(II) hexafluoroacetylacetonate, water, and ammonia as precursors. *J. Electrochem. Soc.*, **153** (3), C146–C151.

- 36 Dasgupta, N.P., Lee, W., and Prinz, F.B. (2009) Atomic layer deposition of lead sulfide thin films for quantum confinement. *Chem. Mater.*, **21** (17), 3973–3978.
- 37 Kukli, K., Peussa, M., Johansson, L.-S., Nykänen, E., and Niinistö, L. (1999) Controlled growth of yttrium oxysulfide thin films by atomic layer deposition. *Mater. Sci. Forum*, **315–317**, 216–221.
- 38 Sarkar, S.K., Kim, J.Y., Goldstein, D.N., Neale, N.R., Zhu, K., Elliott, M., Frank, A.J., and George, S.M. (2010)  $\text{In}_2\text{S}_3$  atomic layer deposition and its application as a sensitizer on  $\text{TiO}_2$  nanotube arrays for solar energy conversion. *J. Phys. Chem. C*, **114** (17), 8032–8039.
- 39 Pilvi, T., Ritala, M., Leskelä, M., Bischoff, M., Kaiser, U., and Kaiser, N. (2008) Atomic layer deposition process with  $\text{TiF}_4$  as a precursor for depositing metal fluoride thin films. *Appl. Opt.*, **47** (13), C271–C274.
- 40 Ylilammi, M. and Ranta-aho, T. (1994) Metal fluoride thin films prepared by atomic layer deposition. *J. Electrochem. Soc.*, **141** (5), 1278–1284.
- 41 Putkonen, M., Szeghalmi, A., Pippel, E., and Knez, M. (2011) Atomic layer deposition of metal fluorides through oxide chemistry. *J. Mater. Chem.*, accepted.
- 42 Gardiner, R., Brown, D.W., Kirilin, P.S., and Rheingold, A.L. (1991) Volatile barium  $\beta$ -diketonate polyether adducts. Synthesis, characterization, and metalloorganic chemical vapor deposition. *Chem. Mater.*, **3** (6), 1053–1059.
- 43 Gordon, R.G., Barry, S., Broomhall-Dillard, R.N.R., and Teff, D.J. (2000) Synthesis and solution decomposition kinetics of flash-vaporizable liquid barium beta-diketonates. *Adv. Mater. Opt. Electron.*, **10** (3), 201–211.
- 44 Hänninen, T., Mutikainen, I., Saanila, V., Ritala, M., Leskelä, M., and Hanson, J.C. (1997)  $[\text{Ca}(\text{Thd})_2(\text{Tetraen})]$ : a monomeric precursor for deposition of  $\text{CaS}$  thin films. *Chem. Mater.*, **9** (5), 1234–1240.
- 45 Putkonen, M., Sajavaara, T., Johansson, L.-S., and Niinistö, L. (2001) Low temperature ALE deposition of  $\text{Y}_2\text{O}_3$  thin films from  $\beta$ -diketonate precursors. *Chem. Vapor Depos.*, **7** (1), 44–50.
- 46 Musschoot, J., Deduytsche, D., Poelman, H., Haemers, J., Van Meirhaeghe, R.L., Van den Berghe, S., and Detavernier, C. (2009) Comparison of thermal and plasma-enhanced ALD/CVD of vanadium pentoxide. *J. Electrochem. Soc.*, **156** (7), P122–P126.
- 47 Kim, J.C., Heo, J.S., Cho, Y.S., and Moon, S.H. (2009) Atomic layer deposition of an  $\text{HfO}_2$  thin film using  $\text{Hf}(\text{O}-i\text{Pr})_4$ . *Thin Solid Films*, **517** (19), 5695–5699.
- 48 Pore, V., Rahtu, A., Leskelä, M., Ritala, M., Sajavaara, T., and Keinonen, J. (2004) Atomic layer deposition of photocatalytic  $\text{TiO}_2$  thin films from titanium tetramethoxide and water. *Chem. Vapor Depos.*, **10** (3), 143–148.
- 49 Aarik, J., Aidla, A., Sammelselg, V., Uustare, T., Ritala, M., and Leskelä, M. (2000) Characterization of titanium dioxide atomic layer growth from titanium ethoxide and water. *Thin Solid Films*, **370** (12), 163–172.
- 50 Kim, S.K., Choi, G.J., Kim, J.H., and Hwang, C.S. (2008) Growth behavior of Al-doped  $\text{TiO}_2$  thin films by atomic layer deposition. *Chem. Mater.*, **20** (11), 3723–3727.
- 51 Xie, Q., Musschoot, J., Deduytsche, D., Van Meirhaeghe, R.L., Detavernier, C., Van den Berghe, S., Jiang, Y.-L., Ru, G.-P., Li, B.-Z., and Qu, X.-P. (2008) Growth kinetics and crystallization behavior of  $\text{TiO}_2$  films prepared by plasma enhanced atomic layer deposition. *J. Electrochem. Soc.*, **155** (9), H688–H692.
- 52 Vehkamäki, M., Hänninen, T., Ritala, M., Leskelä, M., Sajavaara, T., Rauhala, E., and Keinonen, J. (2001) Atomic layer deposition of  $\text{SrTiO}_3$  thin films from a novel strontium precursor strontium bis (tri-isopropyl cyclopentadienyl). *Chem. Vapor Depos.*, **7** (2), 75–80.
- 53 Lee, J.H., Cho, Y.J., Min, Y.S., Kim, D., and Rhee, S.W. (2002) Plasma enhanced atomic layer deposition of  $\text{SrTiO}_3$  thin films with  $\text{Sr}(\text{tmhd})_2$  and  $\text{Ti}(i\text{-OPr})_4$ . *J. Vac. Sci. Technol. A*, **20** (5), 1828–1830.
- 54 Hatanpää, T., Vehkamäki, M., Ritala, M., and Leskelä, M. (2010) Study of bismuth alkoxides as possible precursors for ALD. *Dalton Trans.*, **39** (13), 3219–3226.
- 55 Bachmann, J., Jing, J., Knez, M., Barth, S., Shen, H., Mathur, S., Gösele, U., and

- Nielsch, K. (2007) Ordered iron oxide nanotube arrays of controlled geometry and tunable magnetism by atomic layer deposition. *J. Am. Chem. Soc.*, **129** (31), 9554–9555.
- 56 Putkonen, M., Aaltonen, T., Alnes, M., Sajavaara, T., Nilsen, O., and Fjellvåg, H. (2009) Atomic layer deposition of lithium containing thin films. *J. Mater. Chem.*, **19**, 8767–8771.
- 57 Jones, A.C., Aspinall, H.C., Chalker, P.R., Potter, R.J., Manning, T.D., Loo, Y.F., O’Kane, R., Gaskell, J.M., and Smith, L.M. (2006) MOCVD and ALD of high-*k* dielectric oxides using alkoxide precursors. *Chem. Vapor Depos.*, **12** (2–3), 83–98.
- 58 Yang, T.S., Cho, W., Kim, M., An, K.-S., Chung, T.-M., Kim, C.G., and Kim, Y. (2005) Atomic layer deposition of nickel oxide films using Ni(dmamp)<sub>2</sub> and water. *J. Vac. Sci. Technol.*, **23** (4), 1238–1243.
- 59 Lee, J.P., Park, M.H., Chung, T.-M., Kim, Y., and Sung, M.M. (2004) Atomic layer deposition of TiO<sub>2</sub> thin films from Ti (O<sup>i</sup>Pr)<sub>2</sub>(dmae)<sub>2</sub> and H<sub>2</sub>O. *Bull. Korean Chem. Soc.*, **25** (4), 475–479.
- 60 Bachmann, J., Zierold, R., Chong, J.T., Hauert, R., Sturm, C., Schmidt-Grund, R., Rheinländer, B., Grundmann, M., Gösele, U., and Nielsch, K. (2008) A practical, self-catalytic, atomic layer deposition of silicon dioxide. *Angew. Chem., Int. Ed.*, **47**, 6177–6179.
- 61 Ferguson, J.D., Smith, E.R., Weimer, A.W., and George, S.M. (2004) Atomic layer deposition of SiO<sub>2</sub> at room temperature using TEOS and H<sub>2</sub>O with NH<sub>3</sub> as the catalyst. *J. Electrochem. Soc.*, **151** (8), G528–G535.
- 62 Lee, B.H., Hwang, J.K., Nam, J.W., Lee, S.U., Kim, J.T., Koo, S.-M., Baunemann, A., Fischer, R.A., and Sung, M.M. (2009) Low-temperature atomic layer deposition of copper metal thin films: self-limiting surface reaction of copper dimethylamino-2-propoxide with diethylzinc. *Angew. Chem., Int. Ed.*, **48** (25), 4536–4539.
- 63 Becker, J.S., Kim, E., and Gordon, R.G. (2004) Atomic layer deposition of insulating hafnium and zirconium nitrides. *Chem. Mater.*, **16** (18), 3497–3501.
- 64 Kim, J.C., Cho, Y.S., and Moon, S.H. (2009) Atomic layer deposition of HfO<sub>2</sub> onto Si using Hf(NMe<sub>2</sub>)<sub>4</sub>. *Jpn. J. Appl. Phys.*, **48**, 066515–066521.
- 65 Kwon, J., Dai, M., Halls, M.D., Langereis, E., Chabal, Y.J., and Gordon, R.G. (2009) *In situ* infrared characterization during atomic layer deposition of lanthanum oxide. *J. Phys. Chem. C*, **113** (2), 654–660.
- 66 Lee, B., Park, T.J., Hande, S., Kim, M.J., Wallace, R.M., Kim, J., Liu, X., Yi, J.H., Li, H., Rousseau, M., Shenai, D., and Suydam, J. (2009) Electrical properties of atomic-layer-deposited La<sub>2</sub>O<sub>3</sub> films using a novel La formamidinate precursor and ozone. *Microelectron. Eng.*, **86** (7–9), 1658–1661.
- 67 Yang, R.B., Bachmann, J., Reiche, M., Gerlach, J.W., Gösele, U., and Nielsch, K. (2009) Atomic layer deposition of antimony oxide and antimony sulfide. *Chem. Mater.*, **21** (13), 2586–2588.
- 68 Becker, J.S. and Gordon, R.G. (2003) Diffusion barrier properties of tungsten nitride films grown by atomic layer deposition from bis(*tert*-butylimido)bis(dimethylamido) tungsten and ammonia. *Appl. Phys. Lett.*, **82** (14), 2239–2241.
- 69 Miikkulainen, V., Suvanto, M., Pakkanen, T.A., Siitonen, S., Karvinen, P., Kuittinen, M., and Kisonen, H. (2008) Thin films of MoN, WN, and perfluorinated silane deposited from dimethylamido precursors as contamination resistant coatings on micro-injection mold inserts. *Surf. Coat. Technol.*, **202** (21), 5103–5109.
- 70 Kamiyama, S., Miura, T., and Nara, Y. (2006) Comparison between SiO<sub>2</sub> films deposited by atomic layer deposition with SiH<sub>2</sub>[N(CH<sub>3</sub>)<sub>2</sub>]<sub>2</sub> and SiH[N(CH<sub>3</sub>)<sub>2</sub>]<sub>3</sub> precursors. *Thin Solid Films*, **515** (4), 1517–1521.
- 71 Burton, B.B., Kang, S.W., Rhee, S.W., and George, S.M. (2009) SiO<sub>2</sub> atomic layer deposition using tris(dimethylamino) silane and hydrogen peroxide studied by *in situ* transmission FTIR spectroscopy. *J. Phys. Chem. C*, **113** (19), 8249–8257.
- 72 Suzuki, I., Yanagita, K., and Dussarrat, C. (2007) Extra low-temperature SiO<sub>2</sub> deposition using aminosilanes. *ECS Trans.*, **3**, 119–128.
- 73 Rees, W.S., Jr., Just, O., and van Derveer, D.S. (1999) Molecular design of dopant

- precursors for atomic layer epitaxy of SrS: *Ce. J. Mater. Chem.*, **9**, 249–252.
- 74 He, W., Schuetz, S., Solanki, R., Belot, J., and McAndrew, J. (2004) Atomic layer deposition of lanthanum oxide films for high-kappa gate dielectrics. *Electrochem. Solid-State Lett.*, **7** (7), G131–G133.
  - 75 Vehkamäki, V.M., Hatanpää, T., Kemell, M., Ritala, M., and Leskelä, M. (2006) Atomic layer deposition of ferroelectric bismuth titanate  $\text{Bi}_4\text{Ti}_3\text{O}_{12}$  thin films. *Chem. Mater.*, **18** (16), 3883–3888.
  - 76 Nam, W.-H. and Rhee, S.-W. (2010) Atomic layer deposition of  $\text{ZrO}_2$  thin films using dichlorobis[tris-(trimethylsilyl)amido]zirconium and water. *Chem. Vapor Depos.*, **10** (4), 201–205.
  - 77 Lim, B.S., Rahtu, A., Park, J.-S., and Gordon, R. (2003) Synthesis and characterization of volatile, thermally stable, reactive transition metal amidinates. *Inorg. Chem.*, **42** (24), 7951–7958.
  - 78 Wang, H., Gordon, R.G., Alvis, R., and Ulfig, R.M. (2009) Atomic layer deposition of ruthenium thin films from an amidinate precursor. *Chem. Vapor Depos.*, **15** (10–12), 312–319.
  - 79 Milanov, A.P., Xu, K., Laha, A., Bugiel, E., Ranjith, R., Schwendt, D., Osten, H.J., Parala, H., Fischer, R.A., and Devi, A. (2010) Growth of crystalline  $\text{Gd}_2\text{O}_3$  thin films with a high-quality interface on Si (100) by low-temperature  $\text{H}_2\text{O}$ -assisted atomic layer deposition. *J. Am. Chem. Soc.*, **132** (1), 36–37.
  - 80 Barreca, D., Milanov, A., Fischer, R.A., Devi, A., and Tondello, E. (2009) Hafnium oxide thin film grown by ALD: an XPS study. *Surf. Sci. Spectra*, **14** (1), 34–40.
  - 81 Saly, M.J., Munnik, F., Baird, R.J., and Winter, C.H. (2009) Atomic layer deposition growth of  $\text{BaB}_2\text{O}_4$  thin films from an exceptionally thermally stable tris (pyrazolyl)borate-based precursor. *Chem. Mater.*, **21** (16), 3742–3744.
  - 82 Pore, V., Hatanpää, T., Ritala, M., and Leskelä, M. (2009) Atomic layer deposition of metal tellurides and selenides using alkylsilyl compounds of tellurium and selenium. *J. Am. Chem. Soc.*, **131** (10), 3478–3480.
  - 83 Yokoyama, H., Tanimoto, M., Shinohara, M., and Inoue, N. (1994) Self-limiting and step-propagating nature of GaAs atomic layer epitaxy revealed by atomic force microscopy. *Appl. Surf. Sci.*, **82/83**, 158–163.
  - 84 Reidl, J.G., Uridianyk, H.M., and Bedair, S.M. (1991) Role of trimethylgallium exposure time in carbon doping and high temperature atomic layer epitaxy of GaAs. *Appl. Phys. Lett.*, **59** (19), 2397–2399.
  - 85 Simko, J.P., Meguro, T., Iwai, S., Ozasa, K., Aoyagi, Y., and Sugano, T. (1993) Surface photo-absorption study of the laser-assisted atomic layer epitaxial growth process of GaAs. *Thin Solid Films*, **225** (1–2), 40–46.
  - 86 Jeong, W.G., Menu, E.P., and Dapkus, P.D. (1989) Steric hindrance effects in atomic layer epitaxy of InAs. *Appl. Phys. Lett.*, **55**, 244–246.
  - 87 Pan, N., Carter, J., Hein, S., Howe, D., Goldman, L., Kupferberg, L., Brierley, S., and Hsieh, K.C. (1993) Atomic layer epitaxy of InP using trimethylindium and tertiarybutylphosphine. *Thin Solid Films*, **225** (1–2), 64–69.
  - 88 Ott, A.W., Johnson, J.M., Klaus, J.W., and George, S.M. (1997) Surface chemistry of  $\text{In}_2\text{O}_3$  deposition using  $\text{In}(\text{CH}_3)_3$  and  $\text{H}_2\text{O}$  in a binary reaction sequence. *Appl. Surf. Sci.*, **112**, 205–215.
  - 89 Hirose, S., Yoshida, A., Yamaura, M., Kano, N., and Munekata, H. (1995) Control of carbon incorporation in AlAs grown by atomic layer epitaxy using variously orientated substrates. *J. Mater. Sci.*, **11** (1), 7–10.
  - 90 Ishii, M., Iwai, S., Ueki, T., and Aoyagi, Y. (1998) Surface reaction mechanism and morphology control in AlP atomic layer epitaxy. *Thin Solid Films*, **318**, 6–10.
  - 91 Lee, Y.J. and Kang, S.-W. (2004) Growth of aluminum nitride thin films prepared by plasma-enhanced atomic layer deposition. *Thin Solid Films*, **446** (2), 227–231.
  - 92 Kukli, K., Ritala, M., Leskelä, M., and Jokinen, J. (1997) Atomic layer epitaxy growth of aluminum oxide thin films from a novel  $\text{Al}(\text{CH}_3)_2\text{Cl}$  precursor and  $\text{H}_2\text{O}$ . *J. Vac. Sci. Technol. A*, **15** (4), 2214–2218.

- 93 Huang, R. and Kitai, A.H. (1993) Preparation and characterization of thin films of  $\text{MgO}$ ,  $\text{Al}_2\text{O}_3$  and  $\text{MgAl}_2\text{O}_4$  by atomic layer deposition. *J. Electron. Mater.*, **22** (2), 215–220.
- 94 Puurunen, R. (2005) Surface chemistry of atomic layer deposition: a case study for the trimethylaluminum/water process. *Appl. Phys. Rev.*, **97** (12), 121301-1–121301-52.
- 95 Fan, J.-F., Toyoda, K. (2005) (1992) Self-limiting behavior of the growth of  $\text{Al}_2\text{O}_3$  using sequential vapor pulses of TMA and  $\text{H}_2\text{O}_2$ . *Appl. Surf. Sci.*, **60–61**, 765–769.
- 96 Drozd, V.E., Baraban, A.P., and Nikiforova, I.O. (1994) Electrical properties of  $\text{Si-Al}_2\text{O}_3$  structures grown by ML-ALE. *Appl. Surf. Sci.*, **82–83**, 583–586.
- 97 Kumagai, H., Toyoda, K., Matsumoto, M., and Obara, M. (1993) Comparative study of  $\text{Al}_2\text{O}_3$  optical crystalline thin films grown by vapor combinations of  $\text{Al}(\text{CH}_3)_3/\text{N}_2\text{O}$  and  $\text{Al}(\text{CH}_3)_3/\text{H}_2\text{O}_2$ . *Jpn. J. Appl. Phys.*, **32**, 6137–6140.
- 98 Jeong, C.-W., Lee, J.-S., and Joo, S.-K. (2001) Plasma-assisted atomic layer growth of high-quality aluminum oxide thin films. *Jpn. J. Appl. Phys.*, **40**, 285–289.
- 99 Elliot, S.D., Scarel, G., Wiemer, C., Fanciulli, M., and Pavia, G. (2006) Ozone-based atomic layer deposition of alumina from TMA: growth, morphology, and reaction mechanism. *Chem. Mater.*, **18** (16), 3764–3773.
- 100 Drozd, V.E. and Aleskovski, V.B. (1994) Synthesis of conducting oxides by ML-ALE. *Appl. Surf. Sci.*, **82–83**, 591–594.
- 101 Yousfi, E.B., Asikainen, T., Pietu, V., Cowache, P., Powalla, M., and Lincot, D. (2000) Cadmium-free buffer layers deposited by atomic later epitaxy for copper indium diselenide solar cells. *Thin Solid Films*, **361–362**, 183–186.
- 102 Yokoyama, M., Chen, N.T., and Ueng, H.Y. (2000) Growth and characterization of  $\text{ZnSe}$  on  $\text{Si}$  by atomic layer epitaxy. *J. Cryst. Growth*, **212** (1), 97–102.
- 103 Wang, W.-S., Ehsani, H., and Bhat, I. (1993) Improved  $\text{CdTe}$  layers on  $\text{GaAs}$  and  $\text{Si}$  using atomic layer epitaxy. *J. Electron. Mater.*, **22** (8), 873–878.
- 104 Sang, B., Yamada, A., and Konagai, M. (1997) Growth of boron-doped  $\text{ZnO}$  thin films by atomic layer deposition. *Sol. Energy Mater. Sol. Cells*, **49** (1–4), 19–26.
- 105 Saito, K., Hiratsuka, Y., Omata, A., Makino, H., Kishimoto, S., Yamamoto, T., Horiuchi, N., and Hirayama, H. (2007) Atomic layer deposition and characterization of Ga-doped  $\text{ZnO}$  thin films. *Superlatt. Microstruct.*, **42** (1–6), 172–175.
- 106 Lujala, V., Skarp, J., Tammenmaa, M., and Suntola, T. (1994) Atomic layer epitaxy growth of doped zinc oxide thin films from organometals. *Appl. Surf. Sci.*, **82–83**, 34–40.
- 107 Yun, S.J., Kim, Y.S., and Park, S.-H.K. (2001) Fabrication of  $\text{CaS:Pb}$  blue phosphor by incorporating dimeric  $\text{Pb}^{2+}$  luminescent centers. *Appl. Phys. Lett.*, **78** (6), 721–723.
- 108 Long, N.J. (1998) *Metallocenes: An Introduction to Sandwich Compounds*, Blackwell Science Ltd, Oxford.
- 109 Weber, A., Suhr, H., Schumann, H., Köhn, R.-D. (1990) Thin yttrium and rare earth oxide films produced by plasma enhanced CVD of novel organometallic  $\pi$ -complexes. *Appl. Phys. A*, **51** (6), 520–525.
- 110 Russell, D.K. (1996) Gas-phase pyrolysis mechanisms in organometallic CVD. *Chem. Vapor Depos.*, **2** (6), 223–233.
- 111 Putkonen, M., Sajavaara, T., and Niinistö, L. (2000) Enhanced growth rate in atomic layer epitaxy deposition of magnesium oxide thin films. *J. Mater. Chem.*, **10**, 1857–1861.
- 112 Huang, R. and Kitai, A.H. (1992) Temperature-dependence of the growth orientation of atomic layer growth  $\text{MgO}$ . *Appl. Phys. Lett.*, **61** (12), 1450–1452.
- 113 Vehkamäki, M., Hänninen, T., Ritala, M., Leskelä, M., Sajavaara, T., Rauhala, E., and Keinonen, J. (2001) Atomic layer deposition of  $\text{SrTiO}_3$  thin films from a novel strontium precursor: strontium-bis (tri-isopropyl cyclopentadienyl). *Chem. Vapor Depos.*, **7** (2), 75–80.
- 114 Ihanus, J., Hänninen, T., Hatanpää, T., Aaltonen, T., Mutikainen, I., Sajavaara, T., Keinonen, J., Ritala, M., and Leskelä, M. (2002) Atomic layer deposition of  $\text{SrS}$  and  $\text{BaS}$  thin films using cyclopentadienyl precursors. *Chem. Mater.*, **14** (5), 1937–1944.

- 115 Putkonen, M., Nieminen, M., Niinistö, J., Sajavaara, T., and Niinistö, L. (2001) Surface-controlled deposition of  $\text{Sc}_2\text{O}_3$  thin films by atomic layer epitaxy using  $\beta$ -diketonate and organometallic precursors. *Chem. Mater.*, **13** (12), 4701–4707.
- 116 Kim, W.-S., Park, S.-K., Moon, D.-Y., Kang, B.-W., Kim, H.-D., and Park, J.-W. (2009) Characteristics of  $\text{La}_2\text{O}_3$  thin films deposited using the ECR atomic layer deposition method. *J. Korean Phys. Soc.*, **55** (2), 590–593.
- 117 Lau, J.E., Peterson, G.G., Endisch, D., Barth, K., Topol, A., Kaloyeros, A.E., Tuenge, R.T., and King, C.N. (2001) *In situ* studies of the nucleation mechanisms of tris(cyclopentadienyl)cerium as cerium dopant source in  $\text{SrS}:\text{Ce}$  thin films for electroluminescent displays. *J. Electrochem. Soc.*, **148** (6), C427–C432.
- 118 Katamreddy, R., Stafford, N.A., Guerin, L., Feist, B., Dussarrat, C., Pallem, V., Weiland, C., and Opila, R. (2009) Atomic layer deposition of rare-earth oxide thin films for high- $k$  dielectric applications. *ECS Trans.*, **19** (2), 525–536.
- 119 Putkonen, M. and Niinistö, L. (2001) Zirconia thin films by atomic layer epitaxy. A comparative study on the use of novel precursors with ozone. *J. Mater. Chem.*, **11**, 3141–3147.
- 120 Niinistö, J., Putkonen, M., Niinistö, L., Stoll, S.L., Kukli, K., Sajavaara, T., Ritala, M., and Leskelä, M. (2005) Controlled growth of  $\text{HfO}_2$  thin films by atomic layer deposition from cyclopentadienyl-type precursor and water. *J. Mater. Chem.*, **15** (23), 2271–2275.
- 121 Rose, M., Niinistö, J., Michalowski, P., Gerlich, L., Wilde, L., Endler, I., and Bartha, J.W. (2009) Atomic layer deposition of titanium dioxide thin films from  $\text{Cp}^*\text{Ti}(\text{OME})_3$  and ozone. *J. Phys. Chem. C*, **113** (52), 21825–21830.
- 122 Niinistö, J., Putkonen, M., Niinistö, L., Song, F., Williams, P., Heys, P.N., and Odedra, R. (2007) Atomic layer deposition of  $\text{HfO}_2$  thin films exploiting novel cyclopentadienyl precursors at high temperatures. *Chem. Mater.*, **19** (13), 3319–3324.
- 123 Katamreddy, R., Wang, Z., Omarjee, V., Rao, P.V., Dussarrat, C., and Blasco, N. (2009) Advanced precursor development for Sr and Ti based oxide thin film applications. *ECS Trans.*, **25** (4), 217–230.
- 124 Niinistö, J., Mäntymäki, M., Kukli, K., Costelle, L., Puukilainen, E., Ritala, M., and Leskelä, M. (2010) Growth and phase stabilization of  $\text{HfO}_2$  thin films by ALD using novel precursors. *J. Cryst. Growth*, **312** (1), 245–249.
- 125 Burton, B.B., Fabreguette, F.H., and George, S.M. (2009) Atomic layer deposition of  $\text{MnO}$  using bis(ethylcyclopentadienyl)manganese and  $\text{H}_2\text{O}$ . *Thin Solid Films*, **517** (19), 5658–5665.
- 126 Rooth, M., Johansson, A., Kukli, K., Aarik, J., Boman, M., and Härsta, A. (2008) Atomic layer deposition of iron oxide thin films and nanotubes using ferrocene and oxygen as precursors. *Chem. Vapor Depos.*, **14** (3–4), 67–70.
- 127 Elam, J.W., Martinson, A.B.F., Pellin, M.J., and Hupp, J.T. (2006) Atomic layer deposition of  $\text{In}_2\text{O}_3$  using cyclopentadienyl indium: a new synthetic route to transparent conducting oxide films. *Chem. Mater.*, **18** (15), 3571.
- 128 Chae, J., Park, H.-S., and Kang, S. (2002) Atomic layer deposition of nickel by the reduction of preformed nickel oxide. *Electrochem. Solid-State Lett.*, **5** (10), C64–C66.
- 129 Daub, M., Knez, M., Göesele, U., and Nielsch, K. (2007) Ferromagnetic nanotubes by atomic layer deposition in anodic alumina membranes. *J. Appl. Phys.*, **101** (9), 09J111–09J113.
- 130 Kim, J.-M., Lee, H.-B.-R., Lansalot, C., Dussarat, C., Gatineau, J., and Kim, H. (2010) Plasma-enhanced atomic layer deposition of cobalt using cyclopentadienyl isopropyl acetamidinato-cobalt as a precursor. *Jpn. J. Appl. Phys.*, **49**, 05FA10-1–05FA10-5.
- 131 Aaltonen, T., Ritala, M., Tung, Y.-L., Chi, Y., Arstila, K., Meinander, K., Leskelä, M. (2004) Atomic layer deposition of noble metals: exploration of the low limit of the deposition temperature. *J. Mater. Res.*, **19**, 3353–3358.
- 132 Aaltonen, T., Rahtu, A., Ritala, M., and Leskelä, M. (2003) Reaction mechanism studies on atomic layer deposition of ruthenium and platinum. *Electrochem. Solid-State Lett.*, **6** (9), C130–C133.

- 133 Park, S.-J., Kim, W.-H., Lee, H.-B.-R., Maeng, W.J., and Kim, H. (2008) Thermal and plasma enhanced atomic layer deposition ruthenium and electrical characterization as a metal electrode. *Microelectron. Eng.*, **85** (1), 39–44.
- 134 Kim, W.-H., Park, S.-J., Kim, D.Y., and Kim, H. (2009) Atomic layer deposition of ruthenium and ruthenium-oxide thin films by using a Ru(EtCp)<sub>2</sub> precursor and oxygen gas. *J. Korean Phys. Soc.*, **55** (1), 32–37.
- 135 Knoops, H.C.M., Mackus, A.J.M., Donders, M.E., van de Sanden, M.C.M., Notten, P.H.L., and Kessels, W.M.M. (2009) Remote plasma ALD of platinum and platinum oxide films. *Electrochem. Solid-State Lett.*, **12** (7), G34–G36.
- 136 Aaltonen, T., Ritala, M., Sajavaara, T., Keinonen, J., and Leskelä, M. (2003) Atomic layer deposition of platinum thin films. *Chem. Mater.*, **15** (9), 1924–1928.
- 137 Aaltonen, T., Ritala, M., and Leskelä, M. (2005) Atomic layer deposition of noble metals, in *Advanced Metallization Conference 2004 (AMC 2004)* (eds D. Erb, P. Ramm, K. Masu, and A. Osaki), Materials Research Society, pp. 663–667.
- 138 Schuisky, M., Kukli, K., Ritala, M., Härsta, A., and Leskelä, M. (2000) Atomic layer chemical vapor deposition in the Bi–Ti–O system. *Chem. Vapor Depos.*, **6** (3), 139–145.
- 139 Harjuoja, J., Väyrynen, S., Putkonen, M., Niinistö, L., and Rauhala, E. (2006) Crystallization of bismuth titanate and bismuth silicate grown as thin films by atomic layer deposition. *J. Cryst. Growth*, **286** (2), 376–383.
- 140 Ritala, M., Kukli, K., Rahtu, A., Räisänen, P.I., Leskelä, M., Sajavaara, T., and Keinonen, J. (2000) Atomic layer deposition of oxide thin films with metal alkoxides as oxygen sources. *Science*, **288** (5464), 319–321.
- 141 Hausmann, D., Becker, J., Wang, S., and Gordon, R.G. (2002) Rapid vapor deposition of highly conformal silica nanolaminates. *Science*, **298** (5592), 402–406.
- 142 Putkonen, M., Sajavaara, T., Rahkila, P., Xu, L., Cheng, S., Niinistö, L., and Whitlow, H.J. (2009) Atomic layer deposition and characterization of biocompatible hydroxyapatite thin films. *Thin Solid Films*, **517** (20), 5819–5824.
- 143 Juppo, M., Vehkamäki, M., Ritala, M., and Leskelä, M. (1998) Deposition of molybdenum thin films by an alternate supply of MoCl<sub>5</sub> and Zn. *J. Vac. Sci. Technol. A*, **16** (5), 2845–2850.
- 144 Elam, J.W., Nelson, C.E., Grubbs, R.K., and George, S.M. (2001) Kinetics of the WF<sub>6</sub> and Si<sub>2</sub>H<sub>6</sub> surface reactions during tungsten atomic layer deposition. *Surf. Sci.*, **479**, 121–135.
- 145 Alén, P., Juppo, M., Ritala, M., Sajavaara, T., Keinonen, J., and Leskelä, M. (2001) Atomic layer deposition of Ta(Al)N(C) thin films using trimethylaluminum as a reducing agent. *J. Electrochem. Soc.*, **148** (10), G566–G571.
- 146 Kim, S.-H., Kim, S.-K., Kwak, N., Sohn, H., Kim, J., Jung, S.-H., Hong, M.-R., Lee, S.H., and Collins, J. (2006) Atomic layer deposition of low-resistivity and high-density tungsten nitride thin films using B<sub>2</sub>H<sub>6</sub>, WF<sub>6</sub>, and NH<sub>3</sub>. *Electrochem. Solid-State Lett.*, **9** (3), C54–C57.
- 147 Kukli, K., Forsgren, K., Aarik, J., Uustare, T., Aidla, A., Niskanen, A., Ritala, M., Leskelä, M., and Härsta, A. (2001) Atomic layer deposition of zirconium oxide from zirconium tetraiodide, water and hydrogen peroxide. *J. Cryst. Growth*, **231** (1–2), 262–272.
- 148 Delabie, A., Caymax, M., Gielis, S., Maes, J.W., Nyns, L., Popovici, M., Swerts, J., Tielens, H., Peeters, J., and Van Elshocht, S. (2010) Ozone-based metal oxide atomic layer deposition: impact of N<sub>2</sub>/O<sub>2</sub> supply ratio in ozone generation. *Electrochem. Solid-State Lett.*, **13** (6), H176–H178.
- 149 Hiltunen, L., Kattelus, H., Leskelä, M., Mäkelä, M., Niinistö, L., Nykänen, E., Soininen, P., and Tiitta, M. (1991) Growth and characterization of aluminium oxide thin films deposited from various source materials by atomic layer epitaxy and chemical vapor deposition processes. *Mater. Chem. Phys.*, **28** (4), 379–388.
- 150 Mölsä, H., Niinistö, L., and Utriainen, M. (1994) Growth of yttrium oxide thin films from beta-diketonate precursor. *Adv. Mater. Opt. Electron.*, **4** (6), 389–400.
- 151 Hatanpää, T., Ihanus, J., Kansikas, J., Mutikainen, I., Ritala, M., and Leskelä, M. (1999) Properties of [Mg<sub>2</sub>(thd)<sub>4</sub>] as a



- precursor for atomic layer deposition of MgO thin films and crystal structures of  $[\text{Mg}_2(\text{thd})_4]$   $[\text{Mg}_2(\text{thd})_2(\text{EtOH})_2]$ . *Chem. Mater.*, **11**, 1846.
- 152 Liu, X., Ramanathan, S., Longdergan, A., Srivastava, A., Lee, E., Seidel, T.E., Barton, J.T., Pang, D., and Gordon, R.G. (2005) ALD of hafnium oxide thin films from tetrakis(ethylmethylamino)hafnium and ozone. *J. Electrochem. Soc.*, **152** (3), G213–G219.
  - 153 Niinistö, J., Putkonen, M., Niinistö, L., Arstila, K., Sajavaara, T., Lu, J., Kukli, K., Ritala, M., and Leskelä, M. (2006)  $\text{HfO}_2$  films grown by ALD using cyclopentadienyl-type precursors and  $\text{H}_2\text{O}$  or  $\text{O}_3$  as oxygen source. *J. Electrochem. Soc.*, **153** (3), F39–F45.
  - 154 Juppo, M., Alén, P., Ritala, M., and Leskelä, M. (2001) Trimethylaluminum as a reducing agent in the atomic layer deposition of  $\text{Ti}(\text{Al})\text{N}$  thin films. *Chem. Vapor Depos.*, **7** (5), 211.
  - 155 Burton, B.B., Lavoie, A.R., and George, S.M. (2008) Tantalum nitride atomic layer deposition using tris(diethylamido) (*tert*-butylimido)tantalum and hydrazine. *J. Electrochem. Soc.*, **155** (7), D508–D516.
  - 156 Alén, P., Juppo, M., Ritala, M., Leskelä, M., Sajavaara, T., and Keinonen, J. (2002) *tert*-Butylamine and allylamine as reductive nitrogen sources in atomic layer deposition of  $\text{TaN}$  thin films. *J. Mater. Res.*, **17** (1), 107–114.
  - 157 Kim, H. (2003) Atomic layer deposition of metal and nitride thin films: current research efforts and applications for semiconductor device processing. *J. Vac. Sci. Technol. B*, **21** (6), 2231–2261.
  - 158 Elers, K.-E., Winkler, J., Weeks, K., and Marcus, S. (2005)  $\text{TiCl}_4$  as a precursor in the  $\text{TiN}$  deposition by ALD and PEALD. *J. Electrochem. Soc.*, **152** (8), G589–G593.
  - 159 Maeng, W.J. and Kim, H. (2006) Thermal and plasma-enhanced ALD of Ta and Ti oxide thin films from alkylamide precursors. *Electrochem. Solid-State Lett.*, **9** (6), G191–G194.
  - 160 Guziewicz, E., Godlewski, M., Kopalko, K., Lusakowska, E., Dynowska, E., Guziewicz, M., Godlewski, M.M., and Phillips, M. (2004) Atomic layer deposition of thin films of  $\text{ZnSe}$ : structural and optical characterization. *Thin Solid Films*, **446**, 172–177.
  - 161 Nanu, M., Reijnen, L., Meester, B., Schoonman, J., and Goossens, A. (2004)  $\text{CuInS}_2$  thin films deposited by ALD. *Chem. Vapor Depos.*, **10** (1), 45–49.
  - 162 Drozd, V.E., Nikiforova, I.O., Bogevoilnov, V.B., Yafyasov, A.M., Filatova, E.O., and Papazoglou, D. (2009) ALD synthesis of  $\text{SnSe}$  layers and nanostructures. *J. Phys. D*, **42** (12), 125306–125310.
  - 163 Bakke, J.R., King, J.S., Jung, H.J., Sinclair, R., and Bent, S.F. (2010) Atomic layer deposition of  $\text{ZnS}$  via *in situ* production of  $\text{H}_2\text{S}$ . *Thin Solid Films*. doi: 10.1016/j.tsf.2010.03.074.