## Rosato's Plastics Encyclopedia and Dictionary



during 1958; production was by Monsanto Co. using AN plastic "Barex" (Sohia of BP Chemical International) and Du Pont's stretched injection blow molding process. Unfortunately AN, at that time, was not permitted by the FDA to be used because of possible food contamination, thus stopping production in about eight plants on the East Coast. However it was the forerunner of an avalanche of containers to appear commercially in the 1970s and continue thereafter.

**acrylonitrilic** This family of plastics have repeat units that feature a nitrile side group (C=N), such as polyacrylonitrile, polymethacrylonitrile, acrylonitrile-styrene, and acrylonitrile-methylmethacrylate plastics.

## activated diffusion | permeability

activation 1. Basically it is any process whereby a substance is treated to develop adsorptive properties. 2. The process of treating a substance, molecule, or atom by heat, radiation, or the presence of another substance so that the first mentioned substance, molecule, or atom will undergo chemical or physical change more rapidly or completely. As an example, the process of inducing radio-activity in a specimen by bombardment with neutrons or other type of radiation.

**activator** An additive used to promote the curing of thermoset matrix plastics and reducing cure time by increasing the effectiveness of an accelerator.

## 

## adaptive control > control, adaptive

addition polymerization It has been defined by the IUPAC as polymerization, usually to form linear polymers, in which the monomers add together to form the main part of each polymer molecule without the concurrent production of other small molecules such as water. A common type of additional polymerization is olefinic polymerization, in which the monomers are ethylene or its homologs. The term vinyl polymerization is used to denote addition polymerization of vinyl compounds. Similarly, vinyl-type polymerization refers to addition polymerization of monomers having a carbon-to-carbon bond, such as methyl methacrylate, vinylidene chloride, maleic anhydride, or tetrafluoroethylene. These addition polymerizations all involve the formation of polymers having a carbon-to-carbon single bond along the backbone.

In reality the addition-type process can occur in several ways. One way simply involves the external chemical activation of molecules that cause them to start combining with each other in a chain reaction type fashion (by the bonding of atoms directly within the reacting molecule). Another way for an addition polymerization to occur is through a rearrangement of atoms within both reacting molecules. And still a third way is for a molecule composed of a ring of atoms to open and connect with other ring type molecules being opened up under the influence of the proper catalytic activators; again with no net loss of any atoms from the polymer structure.

additive Additives are basically physically dispersed in a plastic matrix without affecting significantly the molecular structure of the plastic (polymer). Cross-linking agents, catalysts, and others normally used in thermoset systems do purposely affect their structure. Additives are normally classified according to their specific functions rather than a chemical basis. It is also convenient to classify them into groups and to subdivide them according to their specific functions, such as: mechanical properties modifiers: reinforcements (fibers, flakes, whiskers, etc.), interfacing agents (makes additives and plastics compatible), toughening agents, plasticizers, blowing agents, particulate fillers, etc; processing aids: lubricants (internal and/or external), processing stabilizers, melt flow promoters, thixotropic agents, etc; surface properties modifiers: adhesion promoters, slip additives, anti-block additives, anti-wear additives, antistatic agents, blowing agents, etc; physical properties modifiers: blowing agents, flame retardants, hollow spheres, particulate fillers, etc; optical properties modifiers: nucleating agents, dyes, pigments, etc; anti-aging additives: fungicides, anti-oxidants, UV stabilizers, etc; reducing formulation/manufacturing costs: particulate fillers, blowing agents, reinforcements, etc; electrical properties modifiers: mineral and/or metallic fillers, glass microballoons, etc; others: biodegradable agents, preset explosive agents, flame retardants, syntactic fillers, foam/blowing agents, etc.

Unfortunately, there is no "ideal additive" since each of the infinite number of end uses will call for a particular set of characteristics, including diverging properties such as mechanical, physical, chemical, and electrical. To be realistic, the most important requirement of any additive is that it should be effective, for the purpose for which it was designed, at an economical level. Recognize that, like a see-saw, improvements in one property can lead to deterioration in others. Furthermore, the effectiveness of compounding additives depends also on correct procedure of incorporation into the

polymer matrix. However, inco tial compatible are required to performance, such as in reinformaterials.

The target is to set up the quired in a compound and whe velop a compromise. Consider given to factors such as: cost, face wetting and bonding, oil all ical resistance, and required factors usually considered, part design requirements, are color tency, density, thermal expansis properties.

The compatibility and diffutives in plastic compounds is not by trial and error. The theories iors do exist so that they can preliminary concepts to meet mance. The number of additive their possible combinations are their compositions are continually basic theories and knowledge of modynamics may be used to determine the compatibility. Compounding

additive concentrate > conc

adduct A chemical addition p

adhere To cause two surfaces gether by adhesion.

adherent A body that is he body, usually by an adhesive; a prepared for bonding. > abher

adhesive One of the most most taken-for-granted applicati adhesives. Adhesive bonding and animal by-products has been ands of years. With the advent and thermoset plastics over teld of adhesives took on a n Adhesives with strengths high metals have been developed. Ac e of plastic adhesives have made bonding of structural parts in appliances, automo bridges, aircraft, missile medical devices, and most other welding and riveting. cans purchased in the been for decades sealed wi replacing soft solders. = 2 rearview mirror seeming the glass windshield; cyano mes are used.

classification based positions are: (1) synthetic states, thermosets, and elastic

The Author: Dominick V. Rosato, 40 Karen Road, Waban, MA 02168, USA

The use of general descriptive names, trademarks, etc., in this publication, even if the former are not especially identified, is not to be taken as a sign that such names, as understood by the Trade Marks and Merchandise Marks Act, may accordingly be used freely by anyone.

While the advice and information in this book are believed to be true and accurate at the date of going to press, neither the authors nor the editor nor the publisher can accept any legal responsibility for any errors or omissions that may be made. The publisher makes no warranty, express or implied, with respect to the material contained herein.

Die Deutsche Bibliothek - CIP-Einheitsaufnahme

Rosato, Dominick V.: [Plastics encyclopedia and dictionary] Rosato's plastics encyclopedia and dictionary/Dominick V. Rosato. – Munich; Vienna; New York; Barcelona: Hanser; New York: Oxford Univ. Press, 1993

ISBN 3-446-16490-1

NE: HST

All rights reserved. No part of this book may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopying or by any information storage and retrieval system, without permission from the publisher.

Typography and production: Charlotte Fabian, Dublin

Copyright © Carl Hanser Verlag, Munich Vienna New York Barcelona 1993 Printed and bound in Germany by Passavia Druckerei GmbH, Passau.